



iJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 3

Issue: I

Month of publication: January 2015

DOI:

www.ijraset.com

Call: ☎ 08813907089

E-mail ID: ijraset@gmail.com

Analyzing Effects of Weld Parameters for Increasing the Strength of Welded Joint on Mild Steel Material by Using the MIG Welding Process

Darshan A. Bhatt¹, Hardik R. Mehta²

Department of Mechanical Engineering, Indus University, India

Abstract: In Manufacturing the Mechanical Components, joining is the most requisite process. Welding is one such permanent type of joining methods which can join two or more different or same material parts. Among different types of welding processes, MIG welding is the most widely used for joining the parts as it has significant advantages as compare with other welding processes? So this Research Paper is based on how to increase the strength of Welding joints by applying the MIG Welding process. To achieve the best possible solution we have conducted series of experiments using Mild Steel (IS 2062) by applying varying welding parameters like voltage, current, welding speed etc.

Keywords: Metal Inert Gas (MIG), Heat Affected Zone (HAZ), American Society of Mechanical Engineers (ASME), Ultimate Tensile Strength (UTS), Brinell Hardness Number (BHN), Direct Current Electrode Positive (DCEP)

I. INTRODUCTION

MIG welding is a welding process in which an electric arc forms between a consumable wire electrode and the work piece metal, which heats the workpiece metals causing them to melt & join. Along with the wire electrode, a shielding gas feeds through the welding gun, which shields the process from contaminants in the air. Four primary methods of metal transfer in MIG called globular, short circuiting, spray and pulsed spray. Nowadays MIG is widely used in various constructions such as steel structures, bridges, autos, motorcycles, construction machinery, pressure vessels and pipelines due to high welding efficiency. The quality of weldments made by MIG is markedly affected by the welding parameters set by a welder like welding current, welding voltage, travel speed, weld joint position, electrode angle.

A. Welding Current

Welding Current used in MIG has the greatest effect on the deposition rate, weld bead size, shape & penetration. In MIG welding metals are generally welded with DCEP (Direct current electrode positive) because it provides the max. heat input to the work & therefore relatively deep penetration can be obtained. When all other welding parameters are held constant, increasing the current will increase the depth and the width of weld penetration & the size of weld bead. If the current is too high, the size of weld bead is large and excessive deep penetration that wastes the filler metal causes burn through & undercut. Too high or too low welding current also affects the strength of weld metal and tensile strength.

B. Welding Voltage

In MIG, the arc voltage has a decided effect upon the penetration bead reinforcement & bead width. By increasing the arc voltage the weld becomes flatter & wider, the penetration increases until an optimum value of the voltage is reached, at which time it begins to decrease. High and low voltage cause an unstable arc on mild steel. Excessive voltage causes the formation of excessive spatter & porosity in fillet welds, it increases undercut and produces concave fillet welds subject to cracking. Low voltage produces narrower beads with greater convexity but an excessive low voltage may cause porosity and overlapping at the edges of the weld bead.

C. Travel Speed

The travel speed is the rate at which arc travels along the workpiece. For a constant given current, slower travel speeds proportionally provide larger beads and higher heat input to the base metals because of the longer heating time. If the travel speed is too slow unusual weld build up occurs which causes poor fusion, lower penetration, porosity, rough uneven bead. Increasing the travel speed shows opposite effects: less weld metal gets deposited with lower heat input that produces a narrower bead with less penetration. Excessively high speed cause high spatter & undercutting and the beads show an irregular form because of very little weld metal deposit per unit length of weld.

International Journal for Research in Applied Science & Engineering Technology (IJRASET)

Material Composition: Mild Steel : IS 2062

Chemical Composition:-

Carbon %	Manganese Max %	Sulphur Max %	Phosphorous Max %	Silicon Max %	Carbon Equivalent
0.23	1.50	0.045	0.045	0.40	0.42
Tolerance +0.02	+0.05	+0.005	+0.005	+0.03	

Table1. chemical composition of IS 2062

Mechanical Properties:

Tensile Strength, Min , MPa	Yield Stress, Min, MPa		
mm	<20 mm	20-40 mm	>40 mm
410	210	205	190

Table2. mechanical properties of IS 2062

II. EXPERIMENTAL SETUP

In this study, the effect of various welding parameters on the weldability of Mild Steel – IS 2062 specimens having dimensions 300mm×300mm×10 mm welded by MIG welding were investigated. The welding current, arc voltage, welding speed are chosen as welding parameters.

Welding Process : MIG Welding.

Welding Parameters - Welding Current , Arc Voltage & Welding Speed.

Dimension : 300mm×300mm×10mm.

Parent Material Grade : IS 2062.

Electrode Wire Specification : Flux Cored Wire AWS A5-20 E-71T-1

Electrode Wire Diameter : 1.2 mm.

Shielding Gas - Carbon-Dioxide CO₂

Equipment: (1) Mig Welding Gun

(2) Mig Welding Apparatus

(3) Pressure Gauge.



Fig. 1 mig welding gun



Fig. 2 mig welding apparatus

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



Fig. 3 pressure gauge

A. Experimental procedure

First all we had analyzed readings of welding parameters which is currently being used in premier engineering limited. Then we had applied the various varying welding parameters for increasing the strength of welding joints in mig welding. Sample marked as '7' mentioned in the 'Experimental Result' table is being used by premier engineering limited. The readings mentioned in table for sample '1-6' are carried by ourselves under proper welding standard and as per our experimental setup. Various readings for 'Sample 1-6' (as mentioned in experimental results table) were carried by varying Welding Current, Arc Voltage and Welding Speeds. The effect of each parameter on the welding joint was scrutinized by keeping the rest two parameters constants (though welding speed solely depends on the welder and can't be held constant). For carrying out experimental analysis the dimensions of Weldments were chosen as 300mm×300mm×10mm according to 'Test Method - ASME SEC 9 ASTM A370'. Two pieces of dimensions 300mm×150mm×10mm were welded together and such seven samples were prepared. The range for the selection of Welding Current and Arc Voltage were chosen by referring to 'Manufacturing Technology Volume-1' by 'P.N. Rao'. For the preparation of each sample, welding was carried out in three passes and a back-chip. For each pass, the readings for Welding Current, Arc Voltage and Welding Speed were noted down and checked the Hardness and U.T.S. of the specimen.

B. Experimental Results

Sample No.	Sr. No.	Welding Current	Welding Voltage	Welding Speed	Ultimate Tensile Strength (Mpa)	Hardness in BHN		
								Average
1.	1.	159	24.4	211.86	496.24	Parent	167,169,167	167.66
	2.	165	24.8	295.27		Weld	228,222,232	227.33
	3.	159	25.8	272.72		HAZ	185,176, 180	180.33
2.	1.	146	24.8	144.02	464.12	Parent	165,165,176	168.66
	2.	155	24.8	295.27		Weld	195,202,200	199
	3.	158	25.7	264.78		HAZ	156,162,165	161
3.	1.	136	26.4	192.79	474.35	Parent	159,161,162	160.66
	2.	145	26.8	246.71		Weld	216,226,228	223.33
	3.	148	27.7	250		HAZ	162,165,169	165.33
4.	1.	136	22.4	180.07	468.75	Parent	139,137,141	139
	2.	145	22.8	206.89		Weld	198,195,201	198
	3.	148	23.7	225.56		HAZ	152,155,155	154
5.	1.	136	24.4	106.53	478.46	Parent	148,151,151	150
	2.	145	24.8	191.57		Weld	225,228,225	226
	3.	148	25.7	195.69		HAZ	176,183,185	181.33
6.	1.	136	24.4	133.33	449.40	Parent	144,147,150	147
	2.	145	24.8	197.88		Weld	195,198,199	197.33
	3.	148	25.7	233.82		HAZ	145,140,145	143.33
7.	1.	136	24.4	196.07	445.96	Parent	159,161,162	160.66
	2.	145	24.8	145.13		Weld	205,203,208	205.33
	3.	148	25.7	204.08		HAZ	153,155,158	155.33

Table3. Experiment result table

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



Fig. 4 Specimen after welding



Fig. 5 Final weld sample



Fig. 6 samples after tensile test

III. RESULTS & DISCUSSION

- A. As compared with sample “7” (company’s own setup), if we increases the welding speed then hardness increases and ultimate tensile strength also increases as this can be shown from sample no.1(experiment result table).
- B. If welding speed increases, and voltage decreases then hardness is going to decreases. This can be shown in sample no.4 as compared with company’s own setup.
- C. If current kept constant and voltage increases along with increase in welding speed, then hardness increases. (sample no.3 and sample no.7)

IV. CONCLUSION

- A. Since from the above results we have concluded that with increasing the welding speed with constant welding voltage and current, hardness increases.
- B. For increasing the efficiency of welded joint, we have to increase the two parameters keeping remaining one constant.
- C. If Voltage decreases and welding Speed increases hardness decreases. If Voltage increases, Current increases and welding speed decreases then hardness decreases.

REFERENCES

- [1] ASM Handbook Volume 6 - Welding , Brazing and Soldering.
- [2] ASM Handbook Volume 20 - Materials Selection and Design.
- [3] AWS Welding Handbook Volume 1 - Welding Science and Technology
- [4] AWS Welding Handbook Volume - 4 Materials and Applications ,Part-1.
- [5] Manufacturing Technology Volume - 1 by P.N. Rao.
- [6] [http://www.migtigarc.co.uk/Intro MIG Welding.pdf](http://www.migtigarc.co.uk/Intro_MIG_Welding.pdf)
- [7] <http://www.kobelco.co.jp/english/welding/events/files/2011GMAW.pdf>
- [8] <http://www.ijest.info/docs/IJEST10-02-04-29.pdf>
- [9] http://en.wikipedia.org/wiki/Gas_metal_arc_welding
- [10] <http://www.indiamart.com/premierengineering-ahmedabad/>



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)