

# A Study on Compressive Strength of Concrete by Partial Replacement of Cement with Dolomite Powder

Shivangi Pandey<sup>1</sup>, Anisha Mire<sup>2</sup>

<sup>1</sup>Mtech. Student(4<sup>th</sup> Sem), <sup>2</sup>Assistant Professor, RSR Rungta College of Engineering and Technology, Bhilai(C.G)

**Abstract:** *The purpose of this project is to describe the effect of dolomite on compressive strength of concrete. Concrete is most widely used as a construction material. Dolomite has some properties similar to cement, therefore partial replacement of cement with dolomite is effective. Dolomite is calcium magnesium carbonate. It is obtain from sedimentary rock called dolostone and from metamorphic rock is called dolomitic marble. The use of dolomite is to reduce the carbon-dioxide gas emission from cement manufacturing and to gain compressive strength. The obtain result will be analysed to get optimum mix with maximum compressive strength.*

**Keywords:** *Dolomite powder, Compressive strength, Replacement, Cement.*

## I. INTRODUCTION

With the increase in developments and innovations there is a huge demand of concrete. The main constituent is cement in concrete, which is manufacture by the process calcinations of calcareous and argillaceous compound at high temperature. In this process large amount of carbon-dioxide gas is release.

It was found that to manufacture 1 ton of cement there is 0.8 tons of carbon-dioxide gas is released. Dolomite has good resistance to weathering and good in dispersibility and wettability.

Dolomite is preferred due to its high surface hardness and density. M20 grade of concrete is made by partial replacement of cement with dolomite for 28 days of its compressive strength. Some investigations confirmed that dolomite powder can be used as a cementitious material to replace cement with dolomite. This paper examine the possibility to use dolomite as a partial replacement of cement.

## II. LITERATURE REVIEWS

- 1) *S. Deepa Balakrishnan., and K. C. Paulose (2013):* “Studied the workability and strength characteristics of self-compacting concrete containing fly ash and dolomite powder”. It has been examine that the use of dolomite impart viscosity to concrete, increase the strength and improves the segregation resistance of concrete.
- 2) *Deepthi C G, Shindon Baby:* “Study on Compressive Strength of Concrete with Dolomite Powder and Crushed Tiles ”. It is found that the use of dolomite powder improves the strength of concrete. It also makes the low cost concrete, which is the half of cement concrete.
- 3) *L. Ranjith Kumar, J. Kiran, P. Rangarajan:* “Properties of Concrete Incorporating Dolomite Powder”. There is a improvement in the strength of concrete with the replacement of cement with dolomite. The optimum 5% of replacement is done and it is observed that 5.84% increase in compression strength and 2.73% increase in flexure strength of concrete. In case of split strength the increment strength is 2.74%.
- 4) *Kamal M.M, et al (2012):* “Evaluated the bond strength of self compacting concrete mixes containing dolomite powder”. The fly ash is used along with the dolomite to increase the bond strength. Several mixes were prepared and test is carried out. The result showed that the bond strength is increased by the replacement of cement with dolomite. All SCC mixers containing dolomite increase the bond strength upto 30% , which is good for design purpose.
- 5) *Preethi G1, Prince Arulraj G2:* “Effect of Replacement of Cement with Dolomite Powder on the Mechanical Properties of Concrete” . the replacement of 10% of cement with dolomite give the efficient mix with M20 grade of concrete. Reduction in the use of cement will be cost effective and also reduce the emission of green-house gas.

### III. CONCLUSION ON LITERATURE REVIEWS

It is found that partial replacement of dolomite with cement in concrete will increase its mechanical strength with optimum mix design. The use of dolomite is good, as it imparts the similar properties that of cement. It occurs in deposits that are large enough to mine. Since the cost of dolomite is less than cement and emission of carbon-dioxide gas reduces. Dolomite acts as a filler material which acts as a volume matrix to reduce the porosity in the concrete. Therefore, it is found that the dolomite is economical and environment friendly if used as the partial replacement of cement with dolomite.

#### A. Problem Identification

Nowadays, there is a huge demand of concrete for construction work so, it is important that the material used should give effective result. The use of dolomite solves the problem regarding strength, cost and most important the reduction of greenhouse gas (carbon-dioxide).

#### B. Future Scope

The use of cement in construction work is to gain the compressive strength. Therefore it is required to make the concrete good enough to bear maximum load with low cost and eco-friendly. In this paper the use of dolomite in different percentages (5%, 10%, 15%, 20%) in concrete to determine the effect in compressive strength with its mechanism. It also deals with the factors affecting compressive strength.

### REFERENCE

- [1] Vol. 5, Issue 9, September 2016 Copyright to IJRASET DOI:10.15680/IJRASET.2016. Study on Compressive Strength of Concrete with Dolomite Powder and Crushed Tiles Deepthi C G1, Shindon Baby
- [2] Olesia Mikhailovaa, Grigory Yakovlev, Irina Maeva, Sergey Senkov, "Effect of Dolomite Limestone Powder on The Compressive Strength of Concrete", International Conference on Modern Building Materials, Structures and Techniques, Vol.57, pp.775-780, 2013.
- [3] Preethi G, Prince Arulraj, "Effect of Replacement of Cement with Dolomite Powder on the Mechanical Properties of Concrete" International Journal of Innovative Science, Engineering & Technology, Vol.2, pp.1083-1088, 2015.
- [4] Salim Barbhuiya, "Effects of fly ash and dolomite powder on the properties of self-compacting concrete", Construction and Building Materials, Vol. 25, pp.3301-3305, 2011.
- [5] S. Deepa Balakrishnan., and K. C. Paulose, "Workability and strength characteristics of self-compacting concrete containing fly ash and dolomite powder", American Journal of Engineering Research (AJER), Vol. 2, pp.43-47, 2013.
- [6] M.S Shetty, Concrete Technology, New Delhi: S.Chand & Company Ltd, 2012.
- [7] IS 456:2000, Recommended code of practice for plain and reinforced concrete, Bureau of Indian Standard, New Delhi
- [8] IS 10262-2009, Recommended guide lines for concrete mix, Bureau of Indian Standard, New Delhi.
- [9] Schone, S., Dienemann, W., Wagner, E., 2011. "Portland dolomite cement as alternative to Portland limestone cement" Proceedings of the 13th International Congress on the Chemistry of Cement (13th ICC), 3-8 July, 2011, Madrid (CD).
- [10] Henning, O., Kudjakow, A., Winkler, K-G., 1980. Influence of dolomite on the hydration of Portland cement, Scientific Journal of the University of Architecture and Civil Engineering in Weimar 4.