

# Optimisation of Spot Welding Parameters of SS-316 Using Response Surface Methodology

Kaushal Singh<sup>1</sup>, Indraj Singh<sup>2</sup>

<sup>1,2</sup> Department of Mechanical Engineering, SLIET, Longowal, Punjab, India

**Abstract:** Resistance Spot Welding (RSW) is a process in which contacting metal surfaces are joined by the heat obtained from resistance to electric current. It is an important joining technique in various manufacturing sector. This is suitable for welding thin work materials when good quality and surface finish are required. This investigation was intended to analyze the effect of squeeze time, weld time and weld current, on weld nugget width, HAZ width, microhardness and tensile shear strength of spot weld on SS316 sheets, keeping electrode tip diameter, hold time and pressure constant. Further best parameter is optimized using Response Surface Methodology (RSM). It is found that with the increase in squeeze time, weld time and weld current all response parameters i.e. nugget width, HAZ width, microhardness and tensile shear strength increases. It is also found that input Current is the most significant factor for all the response parameters followed by weld time and squeeze time. Then, a confirmation test is carried out and error between predicted and experimental values is determined.

**Keywords:** Resistance spot welding, Optimization, RSM, tensile shear strength.

## I. INTRODUCTION

Resistance Spot welding is a welding process in which coalescence is produced by the heat obtained from resistance of the work to the flow of electric current in a circuit of which the work is a part, and by the application of pressure [1]. Heat is developed at the contact surfaces and pressure is applied by the welding machine through the electrodes. No fluxes or filler metals are used. Hence, any chemical or metallurgical properties desired in the weld solely depend upon the elements present in the workpiece itself. A step down transformer is installed inside the machine which provides the current required by transforming the high-voltage and low-amperage power supply to usable high amperages at low voltages. [1] These three factors affect the heat generated in resistance spot welding. It is expressed by the formula  $H = I^2Rt$ . Where, I is the current flowing through the weld zone, R is the effective resistance in the current carrying circuit, and t is the time of current flow through the weld zone. [2] Most commonly we use Spot welding to make welds in Stainless steel sheets. 300 Series austenitic stainless steel has austenite as its primary phase. These are alloys containing chromium and nickel, and sometimes molybdenum and nitrogen, structured around the Type 302 composition of iron, 18% chromium, and 8% nickel. Grade 316 is alloyed with molybdenum (~2–3%) for high-temperature strength, pitting and crevice corrosion resistance. Response surface designs are used to improve, develop, and optimize a process. These designs are used to get an optimal arrangement of the controllable factors. The RSM is very useful to obtain the first order or second order mathematical model of responses. The response surface analysis is carried out with the help of fitted surface. The designs of fitting response surface are known as response surface designs. The Analysis of Variance (ANOVA) consists of simultaneous hypothesis tests to determine whether any of the effect is significant or not. [3]

## II. EXPERIMENTAL PROCEDURE

### A. Materials and Welded Specimens

The work includes the Resistance Spot Welding of SS 316 stainless steel using Response surface methodology. SS316 stainless steel was taken for Resistance spot welding in the form of rectangular sheet and had the following dimensions: Length = 100mm, Width = 45mm, Thickness = 1mm.




Figure 1 SS316 stainless steel work material

Composition of SS316 is shown in table 1. Grade 316 is alloyed with molybdenum (~2–3%) for high-temperature strength, pitting and crevice corrosion resistance.

TABLE I  
Chemical composition of 316 grade stainless steel

Element	C	Mn	Si	Ni	Cr	P	S	Mo	Co	Fe
%	0.06	0.55	0.31	9.17	17.37	0.03	0.008	2.25	0.128	71.20

B. Nugget Geometry Analysis

The specimen spot welded was used to determine the nugget width and HAZ width. The weld surface of the specimen was first polished with the use of polishing machine with emery grit paper size varying from 100 to 1000. Then etchant (Table 2) was used to analyze the image. Then nugget width and HAZ width was determined.




Figure 2 Visual inspection of nugget (Scale 1:1)

TABLE II  
Stainless Steel Etchant (Carpenter 300 series)

Etchant	Composition
Ferric Chloride	1.417 gm
Cupric Chloride	0.4 gm
Alcohol	20.33 ml
HCl	20.33 ml
Nitric Acid	1 ml

Further we used stereozoom under which we observed and measured the weld nugget and HAZ width as shown in fig. 3.




Figure 3 Measurement of various zones of weld nugget (10x optical zoom)

**C. Tension Shear Test**

For tension shear test BiSS nanoservo tensile testing machine was used. At first, the specimen was gripped in the jaw of the machine and then the grip was tightend. Then load was applied till specimen got fractured and data was recorded. Tension shear test is done to measure the strength of the joint under tensile loading. The specimen for tension shear test were lap welded as shown in fig 4.



Figure 4 Tension Shear test specimens

**D. Microhardness Test**

Vickers microhardness test is carried out to determine hardness of the joint. The specimen was held in the vice of the testing machine and a load of 500gm was applied on the specimen. The indenter was placed in a position where hardness is to be checked and then the output values of hardness were noted. For Vickers microhardness test, the welding was done as shown in fig. 5 and 6, and then all the welded specimens were cut along the XY



Figure 5 Vickers Microhardness test specimens




Figure 6 Microhardness welded specimen and its cutting plane XY

**III. RESULTS AND DISCUSSION**

In proposed study, effect of process parameters (Squeeze time, Weld time and Current) on response parameters such as, Tension shear strength, microhardness, nugget width and HAZ width has been studied. Experiments were design using central composite design (20 runs). Response parameters values at different combination Spot welding input parameters are listed in table 3. During Welding higher tension shear strength, microhardness, nugget width and lower Nugget width are indications of better performance. Table 3 shows experimental results for tension shear strength, nugget width, HAZ width and microhardness.

Experimental results for Tension shear strength, nugget width, HAZ width and microhardness

**A. Analysis of Nugget Width**

Nugget width is a variable dependent on three factors-squeeze time, weld time and weld current.

Sr. No.	Input parameters			Response parameters			
	Squeeze time	Weld time	Current	Nugget Width	HAZ Width	Tension Shear Strength	Microhardness
	Cycles	Cycles	kA	mm	mm	kN	VH
1	35	25	3.75	1.66	1.18	5.200	218.80
2	35	25	5.52	2.82	1.48	6.780	252.48
3	30	35	2.70	2.79	1.36	2.723	234.35
4	35	25	3.75	1.94	1.06	4.756	213.50
5	35	41.82	3.75	2.25	1.36	5.194	232.87
6	43.41	25	3.75	3.05	1.38	4.891	224.95
7	40	35	4.8	3.04	1.54	5.913	238.55
8	35	8.18	3.75	1.80	0.29	3.551	210.40
9	35	25	3.75	1.96	1.05	4.964	213.80
10	40	35	2.70	2.86	1.42	3.827	236.65
11	35	25	3.75	2.20	1.04	4.778	240.97
12	30	35	4.80	3.01	1.43	5.810	236.48
13	26.59	25	3.75	1.93	1.00	4.652	207.77
14	30	15	2.70	1.86	0.57	2.541	199.93
15	40	15	2.70	2.00	0.75	3.582	205.93
16	35	25	3.75	1.96	1.05	4.400	213.67
17	35	25	3.75	1.97	1.18	4.876	213.85
18	30	15	4.80	2.50	0.84	5.200	208.40
19	35	25	1.98	1.89	0.82	2.774	210.67
20	40	15	4.8	2.77	1.22	5.470	260.38

TABLE IV Analysis of variance table for Nugget Width response

Factor	Sum of Squares (SS)	Degree of Freedom (DF)	Mean Square (MS)	F-Value	P-Value Prob>F	
Model	3.57	9	0.40	4.97	0.0098	Significant
A-Squeeze time	0.40	1	0.40	4.98	0.0496	
B-Weld time	0.84	1	0.84	10.50	0.0089	
C-Weld current	0.80	1	0.80	10.05	0.0100	
AB	7.813E-003	1	7.813E-003	0.098	0.7611	
AC	1.125E-004	1	1.125E-004	1.406E-003	0.9708	
BC	0.11	1	0.11	1.41	0.2625	
A <sup>2</sup>	0.91	1	0.91	11.42	0.0070	

B <sup>2</sup>	0.11	1	0.11	1.37	0.2682	
C <sup>2</sup>	0.60	1	0.60	7.50	0.0209	
Residual	0.80	10	0.080			
Lack of Fit	0.65	5	0.13	4.43	0.0640	Not significant
Pure Error	0.15	5	0.029			
Cor Total	4.37	19				

The Model F-value of 4.97 implies the model is significant. There is only a 0.98% chance that a "Model F-Value" this large could occur due to noise. Values of "Prob > F" less than 0.0500 indicate model terms are significant. In this case A, B, C, A<sup>2</sup>, C<sup>2</sup> are significant model terms. The "Lack of Fit F-value" of 4.43 implies there is a 6.40% chance that a "Lack of Fit F-value" this large could occur due to noise. Lack of fit is bad -- we want the model to fit. A negative "Pred R-Squared" implies that the overall mean is a better predictor of the response than the current model. "Adeq Precision" measures the signal to noise ratio. A ratio greater than 4 is desirable. The ratio of 6.616 indicates an adequate signal. This model can be used to navigate the design space.

Nugget width of weld metal in coded form,  $Nugget\ width = 1.94 + 0.17 \times A + 0.25 \times B + 0.24 \times C - 0.031 \times A \times B + 3.750E-003 \times A \times C - 0.12 \times B \times C + 0.25 \times A^2 + 0.087 \times B^2 + 0.20 \times C^2$

Nugget width of weld metal in actual form,  $Nugget\ width = 13.22764 - 0.65781 \times Squeeze\ time + 0.045406 \times Weld\ time - 0.89912 \times Weld\ current - 6.25000E-004 \times Squeeze\ time \times Weld\ time + 7.14286E-004 \times Squeeze\ time \times current - 0.011310 \times Weld\ time \times Current + 0.010070 \times Squeeze\ time^2 + 8.73583E-004 \times Weld\ time^2 - 0.18506 \times Weld\ current^2$

The box plot (Figure 7) is a cubic view representing the eight desirable values for 2<sup>3</sup> full factorial experiments at the corners of the cube. Here maximum desirable nugget width is 3.11 mm at coordinates (A+:40, B+:35, C+:4.8).




Figure 7 Cube plot showing desirable values of nugget width

**B. Analysis of HAZ Width**

HAZ width is a variable dependent on three factors-squeeze time, weld time and weld current.

The Model F-value of 28.78 implies the model is significant. There is only a 0.01% chance that a "Model F-Value" this large could occur due to noise. Values of "Prob > F" less than 0.0500 indicate model terms are significant. In this case A, B, C, BC, A<sup>2</sup>, B<sup>2</sup> are significant model terms. The "Lack of Fit F-value" of 2.30 implies the Lack of Fit is not significant relative to the pure error. There

is a 19.14% chance that a "Lack of Fit F-value" this large could occur due to noise. Non-significant lack of fit is good -- we want the model to fit. The "Pred R-Squared" of 0.7854 is in reasonable agreement with the "Adj R-Squared" of 0.9294. "Adeq Precision" measures the signal to noise ratio. A ratio greater than 4 is desirable. The ratio of 19.816 indicates an adequate signal. This model can be used to navigate the design space.

$$\text{HAZ width of weld metal in coded form} = 1.09 + 0.10 \times A + 0.31 \times B + 0.15 \times C - 0.049 \times A \times B + 0.031 \times A \times C - 0.069 \times B \times C + 0.053 \times A^2 - 0.076 \times B^2 + 0.039 \times C^2$$

$$\text{HAZ width of weld metal in actual form} = 1.01466 - 0.12593 \times \text{Squeeze time} + 0.12730 \times \text{Weld time} - 0.16583 \times \text{Weld current} - 9.75000\text{E-}004 \times \text{Squeeze time} \times \text{Weld time} + 5.95238\text{E-}003 \times \text{Squeeze time} \times \text{current} - 6.54762\text{E-}003 \times \text{Weld time} \times \text{Current} + 2.11473\text{E-}003 \times \text{Squeeze time}^2 - 7.61786\text{E-}004 \times \text{Weld time}^2 + 0.035126 \times \text{Weld current}^2$$

TABLE V  
Analysis of variance table for HAZ width response

Factor	Sum of Squares (SS)	Degree of Freedom (DF)	Mean Squares (MS)	F-Value	P-Value	
Model	1.94	9	0.22	28.78	<0.0001	Significant
A-Squeeze time	0.14	1	0.14	18.31	0.0016	
B-Weld time	1.27	1	1.27	169.86	<0.0001	
C-Weld current	0.30	1	0.30	40.66	<0.0001	
AB	0.019	1	0.019	2.54	0.1423	
AC	7.813E-003	1	7.813E-003	1.04	0.3313	
BC	0.038	1	0.038	5.05	0.0485	
A <sup>2</sup>	0.040	1	0.040	5.37	0.0429	
B <sup>2</sup>	0.084	1	0.084	11.16	0.0075	
C <sup>2</sup>	0.022	1	0.022	2.88	0.1203	
Residual	0.075	10	7.494E-003			
Lack Of Fit	0.052	5	0.010	2.30	0.1914	Non significant
Pure Error	0.023	5	4.547E-003			
Cor Total	2.02	19				

The box plot (Figure 8) is a cubic view representing the eight desirable values for 2<sup>3</sup> full factorial experiments at the corners of the cube. Here minimum desirable HAZ width is 0.470 mm at coordinates (A:-30, B:-15, C:-2.7).




Figure 8 Cube plot showing desirable values of HAZ width

C. Analysis of Tension Shear Strength

Tension shear strength is a variable dependent on three factors-squeeze time, weld time and weld current.

The Model F-value of 24.20 implies the model is significant. There is only a 0.01% chance that a "Model F-Value" this large could occur due to noise. Values of "Prob > F" less than 0.0500 indicate model terms are significant. In this case A, B, C, B<sup>2</sup> are significant model terms. The "Lack of Fit F-value" of 2.01 implies the Lack of Fit is not significant relative to the pure error. There is a 23.11% chance that a "Lack of Fit F-value" this large could occur due to noise. Non-significant lack of fit is good -- we want the model to fit. The "Pred R-Squared" of 0.7563 is in reasonable agreement with the "Adj R-Squared" of 0.9166. "Adeq Precision" measures the signal to noise ratio. A ratio greater than 4 is desirable. The ratio of 17.733 indicates an adequate signal. This model can be used to navigate the design space.

$$\text{Tensile shear strength of weld metal in coded factors} = 4.84 + 0.21 \times A + 0.31 \times B + 1.21 \times C - 0.013 \times A \times B - 0.22 \times A \times C + 0.078 \times B \times C - 0.072 \times A^2 - 0.21 \times B^2 - 0.070 \times C^2$$

$$\text{Tensile shear strength of weld metal in actual factors} = -12.57104 + 0.40954 \times \text{Squeeze time} + 0.11884 \times \text{Weld time} + 2.91572 \times \text{Weld current} - 2.60000\text{E-}004 \times \text{Squeeze time} \times \text{Weld time} - 0.042190 \times \text{Squeeze time} \times \text{current} + 7.45238\text{E-}003 \times \text{Weld time} \times \text{Current} - 2.88660\text{E-}003 \times \text{Squeeze time}^2 - 2.13233\text{E-}003 \times \text{Weld time}^2 - 0.063692 \times \text{Weld current}^2$$

TABLE VI  
Analysis of variance table for tension shear strength response

Factor	Sum of Squares (SS)	Degree of Freedom (DF)	Mean Squares (MS)	F-Value	P-Value	
Model	22.94	9	2.55	24.20	<0.0001	Significant
A-Squeeze time	0.62	1	0.62	5.93	0.0352	
B-Weld time	1.32	1	1.32	12.52	0.0054	
C-Weld current	19.83	1	19.83	188.30	<0.0001	
AB	1.352E-003	1	1.352E-003	0.013	0.9120	
AC	0.39	1	0.39	3.73	0.0824	
BC	0.049	1	0.049	0.47	0.5107	
A <sup>2</sup>	0.075	1	0.075	0.71	0.4183	
B <sup>2</sup>	0.66	1	0.66	6.22	0.0318	
C <sup>2</sup>	0.071	1	0.071	0.67	0.4306	
Residual	1.05	10	0.11			
Lack Of Fit	0.70	5	0.41	2.01	0.2311	Not Significant
Pure Error	0.35	5	0.070			
Cor Total	23.99	19				

The box plot (Figure 9) is a cubic view representing the eight desirable values for 2<sup>3</sup> full factorial experiments at the corners of the cube. Here maximum desirable tension shear strength is 6.050 kN at coordinates (A+:30, B+:35, C+:4.8).




Figure 9 Cube plot showing desirable values of tension shear strength

D. Analysis of Microhardness

Microhardness is a variable dependent on three factors-squeeze time, weld time and weld current.

TABLE VII  
Analysis of variance table for microhardness response

Factor	Sum of Squares (SS)	Degree of Freedom (DF)	Mean Squares (MS)	F-Value	P-Value	
Model	4349.64	9	483.29	4.78	0.0113	Significant
A-Squeeze time	609.61	1	609.61	6.02	0.0340	
B-Weld time	872.84	1	872.84	8.63	0.0149	
C-Weld current	1379.67	1	1379.67	13.63	0.0042	
AB	359.25	1	359.25	3.55	0.0889	
AC	261.63	1	261.63	2.59	0.1389	
BC	433.50	1	433.50	4.28	0.0653	
A <sup>2</sup>	0.13	1	0.13	1.241E-003	0.9726	
B <sup>2</sup>	45.23	1	45.23	0.45	0.5189	
C <sup>2</sup>	402.67	1	402.67	3.98	0.0740	
Residual	1011.94	10	101.19			
Lack Of Fit	417.05	5	83.41	0.70	0.6469	Not Significant
Pure Error	594.88	5	118.98			
Cor Total	5361.58	19				



The Model F-value of 4.78 implies the model is significant. There is only a 1.13% chance that a "Model F-Value" this large could occur due to noise. Values of "Prob > F" less than 0.0500 indicate model terms are significant. In this case A, B, C are significant model terms. The "Lack of Fit F-value" of 0.70 implies the Lack of Fit is not significant relative to the pure error. The "Pred R-Squared" of 0.1716 is not as close to the "Adj R-Squared" of 0.6414 as one might normally expect. This may indicate a large block effect or a possible problem with your model and/or data. Things to consider are model reduction, response transformation, outliers, etc. "Adeq Precision" measures the signal to noise ratio. A ratio greater than 4 is desirable. Ther ratio of 8.659 indicates an adequate signal. This model can be used to navigate the design space.

$$\text{Microhardness of nugget in coded factors} = 218.96 + 6.68 \times A + 7.99 \times B + 10.05 \times C - 6.70 \times A \times B + 5.72 \times A \times C - 7.36 \times B \times C - 0.093 \times A^2 + 1.77 \times B^2 + 5.29 \times C^2$$

$$\text{Microhardness of nugget in actual factors} = 150.20768 + 0.86337 \times \text{Squeeze time} + 7.23352 \times \text{Weld time} - 46.98482 \times \text{Weld current} - 0.13403 \times \text{Squeeze time} \times \text{Weld time} + 1.08929 \times \text{Squeeze time} \times \text{current} - 0.70107 \times \text{Weld time} \times \text{Current} - 3.73346E-003 \times \text{Squeeze time}^2 + 0.017717 \times \text{Weld time}^2 + 4.79454 \times \text{Weld current}^2$$

The box plot (Figure 10) is a cubic view representing the eight desirable values for 2<sup>3</sup> full factorial experiments at the corners of the cube. Here maximum desirable microhardness is 248.15 VH at coordinates (A+:40, B+:15, C+:4.8).




Figure 10 Cube plot showing desirable values of microhardness

E. Optimization of Input Parameters

To achieve a optimum value for input parameters so that we get a better nugget width without expulsion of metal, lesser HAZ width and maximum tension shear strength, cross tension strength and microhardness we use desirability in Design Expert.

TABLE VIII  
Desirability table

Constraints	Goal	Lower limit	Upper limit
Nugget width (mm)	Maximize	1.66	3.05
HAZ width (mm)	Minimize	0.29	1.54
Tension shear strength (kN)	Maximize	2.541	6.78
Microhardness ( VH)	Maximize	199.93	260.38

F. Solution

We get 21 solutions with varying desirability but the best suited and with maximum desirability percentage of 60.1 percent we use for further treatment. The optimized experimental value for maximum desirability can be seen in table 9.

TABLE IX  
Optimized result

RUN NO	SQUEEZE TIME (cycles)	WELD TIME (cycles)	WELD CURRENT (kA)	NUGGET WIDTH (mm)	HAZ WIDTH (mm)	TENSION SHEAR STRENGTH (kN)	MICROHARDNESS (VH)
1	40	15	4.8	2.80155	1.19895	5.30272	254.447

**G. Confirmation Test**

Confirmation tests were conducted so as to check whether the combination of optimal parameters produce the values of tension shear strength, nugget width, HAZ width and microhardness as nearby the value found out by the desirability test. The result along with the comparison is shown in table 10..

TABLE X  
Confirmation Test

RESPONSE	PREDICTION	EXPERIMENTATION
Tension Shear Strength (kN)	5.30272	5.123
Nugget Width(mm)	2.80155	2.64
HAZ Width(mm)	1.19895	1.25
Microhardness(VH)	254.447	239.36

Here, by comparing the predicted and experimental values, we can say that the experimental values of Tension Shear Strength, Nugget Width , HAZ width and microhardness differ from the predicted values by a little amount. Hence we can say that the predicted and experimental values almost agree with each other in terms of values.

A confirmation test is carried out to validate the analysis. Confirmation tests showed an error of 3.3% , 5.76% , 4.25% and 5.93% between the predicted and experimental values of tension shear strength , nugget Width , HAZ Width and microhardness respectively which was in acceptable range.

**IV. CONCLUSION**

Based on the achieved results following conclusions can be drawn :

- A. All three independent parameters (current, Squeeze time and weld time) seem to be the influential parameters. The relationship between the input parameters and the response parameters has been developed. The predicted results appeared to be in good agreement with the measured ones.
- B. It is found that with the increase in squeeze time, weld time and weld current all reponse parameters i.e. nugget width, HAZ width, microhardness and tensile shear strength increases.
- C. From the mathematical model so developed, the input Current appears to be the most significant factor for all the response parameters (Tension shear strength, nugget width, HAZ width and microhardness).
- D. Corresponding to highest desirability (maximum tension shear strength, nugget width, microhardness and minimum HAZ width), optimal combination of the input spot welding parameters appears to be Current = 4.8 kA, Weld time = 15 cycles, and Squeeze time = 40 cycles and the optimized value of nugget width, HAZ width, tension shear strength and microhardness are 2.80155 mm, 1.19895 mm, 5.30272 kN and 254.447 VH respectively.
- E. A confirmation tests carried out to validate the predicted results display an error of 3.3% , 5.76% , 4.25% and 5.93% between the predicted and experimental values of tension shear strength , nugget Width , HAZ Width and microhardness respectively which is in acceptable range.

**REFERENCES**

- [1] Parmar RS. Welding Engineering and Technology. Edition 2<sup>nd</sup>, editor. Khanna Publishers; 2010. Page 23-32
- [2] Parmar RS. Welding Processes and Technology. Edition 3<sup>rd</sup>, editor. Khanna Publishers; 2003. Page 328-356
- [3] Montgomery D. Design and Analysis of Experiments. 2008
- [4] Bilici M.K., Yukler A.I. and Kurtulmus M. (2011)' The optimization of welding parameters for friction stir spot welding of high density polyethylene sheets' , Materials and Design 32 4074–4079
- [5] Kahraman N.and Bugra A.S. (2007)' The influence of welding parameters on the joint strength of resistance spot-welded titanium sheets', Materials and Design 28 420–427
- [6] Bilici M.K., and Yukler A.I.(2012)' Effects of welding parameters on friction stir spot welding of high density polyethylene sheets' Materials and Design 33 545–550
- [7] Zhang Z., Yang X., Zhang J., Zhou G., Xu X. and Zou B. (2011)' Effect of welding parameters on microstructure and mechanical properties of friction stir spot welded 5052 aluminum alloy' Materials and Design 32 4461–4470



- [8] Floreaa R.S, Bammanna D.J, Yeldella A., Solankic K.N. andHammia Y. (2013)' Welding parameters influence on fatigue life and microstructure in resistance spot welding of 6061-T6 aluminum alloy' *Materials and Design* 45 456–465
- [9] Shia H., Qiua R., Zhua J., Zhanga k., Yua H. and Dinga G. (2010) ' Effects of welding parameters on the characteristics of magnesium alloy joint welded by resistance spot welding with cover plates' *Materials and Design* 31 4853–4857
- [10] Eisazadeha H., Hamedib M. and Halvaea A. (2010)' New parametric study of nugget size in resistance spot welding process using finite element method' *Materials and Design* 31 149–157
- [11] Houa Z., Kimb I.S., Wanga Y., Lic C. and Chena C. (2007)' Finite element analysis for the mechanical features of resistance spot welding process' *Journal of Materials Processing Technology* 185 160–165