



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 **Issue:** IX **Month of publication:** September 2022

DOI: <https://doi.org/10.22214/ijraset.2022.46661>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Value-Added Products of Rice Husk in Various Disciplines

Anamika¹, Syed A.R. Ahmad², Suresh Jatawa³, V. A. Selvi⁴, Archana Tiwari⁵

^{1,2,3,5} School of Biotechnology, Rajiv Gandhi Proudyogiki Vishvavidyalaya, Bhopal, India

⁴CSIR- Central Institute of Mining and Fuel Research, Digwadih Campus, Dhanbad, India

Abstract: *Oryza sativa* is a highly produced crop for human consumption and survival so as the most ever waste-generating crop in Asian parts of the world, this creates problems due to its ancient disposal system that occupies large spaces and harms the environment in many ways. Thus, in order to present this waste as a golden opportunity for economic development and sustainable development, this review aims to mention different value-added products like bioadsorbent, biofertilizers, bioinsulators, and superhydrophobic coatings that would show a great utilization of agricultural waste. One of the most studied products is bioadsorbent showing a very high absorbing capacity towards methylene blue and As (V) in the groups of dyes and metals respectively. Biofertilizers are found to be a good and better alternative to chemical fertilizers by having higher shelf life and a good carrier of microbes. Due to very high silica content, Rice Husk was found to be a better bioinsulators on the basis of lower thermal conductivity properties. This presence of silica which gives sufficient roughness also made it possible to produce superhydrophobic coatings better than other coatings. All four products have been thoroughly reviewed, which still require further research for other value value-added products. This review can give a most important direction towards lignocellulosic biomass utilization in different applications rather than just using it in the production of biofuel.

Keywords: *Rice Husk Value-Added Products, Bioadsorbent, Biofertilizers, Bioinsulators, and Superhydrophobic coatings.*

I. INTRODUCTION

Oryza sativa is one of the most grown crops in different regions [1] which covers approximately 1% of the earth's surface [2]. These are specially cultivated in Asian countries[3]. Due to the presence of various nutrients (such as carbohydrates, amino acids such as lysine as a first limiting amino acid, and beta-carotene as vitamin A precursor), it supplements people with calories and is very much favorable in growing children [4], [3].

A. Global Trade of Rice

According to FAO, in 2021, the production of rice worldwide has increased by 2.2 million tons from the year 2019 to 2020. Utilization in 2020/21 reached a record level of 514 million tons driven mainly by food use and a mild recovery in non-food uses of rice, for animal feed in particular. World trade of rice in 2021 (January-December) remains largely unvaried at 48 million tons. In the year 2020, India produced a record high of 182.2 million tons of paddy, whereas China, the output of paddy was estimated at 211.9 million tons, indicating being the world's largest rice producer of rice/paddy whereas India is the second [5], [6]. 90% of the total global rice is produced from Asian regions. Rice plays a very important role in the world economy [7] but exports from China and India are relatively low due to their huge population needs [8].

B. Processing of Rice

Rice is a monocotyledon plant with the genus *Oryza* having two further two species, namely *Sativa* and *glaberrima*, natively found in Asia and Africa, respectively [8], [9]. Rice belongs to the grass family (Poaceae) [10]. There are 21 wild species too [9]. *O. sativa* has high quality and yield and is commercially grown in 112 countries.

Grains of rice have different components as layers [3]. Rice kernels are mainly composed of Rice Husk, rice bran, and starchy endosperm having a portion of approximately 20%, 11%, and 69% respectively [12] which is produced by ideal milling. Rice milling is called as a process of removal or separation of husk and bran to obtain the edible portion for consumption [12]. Husk and brown rice together makes the paddy rice produced just after the threshing process. After husk removal, brown rice is produced consisting of bran layer, germ, and the endosperm part (white rice). Brown rice is milled further to remove the bran layer and germ to produce white rice [12], [13]. Fully milled rice contains whole and broken grains [12]. Thus, rice grains need to undergo different milling steps. A common rice milling system is a multi-stage process [16]. This machine separates all the side products like straw, dust, sand, stones, etc., from paddy [17].

Rice Milling has three general stages:

- 1) The cleaning [18] and husk removal stage is also called shelling [13] by *Paddy Husker* or *Paddy Sheller* [17].
- 2) The scouring [18] / bran removal (whitening) and polishing stage by *Rice Polisher* [17] and
- 3) The grading- broken and head rice is separated [13], blending, and packaging stage [12] for dust-free bagging [13].

This milling process is needed to be handled with care to prevent breakage of the kernel and improve the recovery of rice. Rice quality and its value are determined mainly by milling process quality to meet the consumer's preference for polished grain over rough grain [19]. The milling process also plays a role in improving rice nutrition, cook time, and sensory characteristics [20].

C. By-Products of Rice Milling

The major product of rice milling is rice (endosperm) with a yield of 70 %, and the rest 30% is the unconsumed portion of paddy produced as a by-product which includes Rice Husk, rice bran, and rice germ [3]. The rice by-products are divided into two categories i.e., starch-rich and lignocellulosic substrate. Starch-rich category includes rice bran, broken, unripe and discolored rice whereas the lignocellulosic substrate includes Rice Husk [21]. Traditionally, these byproducts were considered waste which led to indiscriminate burning of the waste resulting in environmental pollution [22].

If these byproducts could have alternative utilization, then could promote improved yield and sustainable rice production as an economic booster for rice-producing nations [23], [20]. In recent years, rice by-products have attracted very high attention as functional foods due to their high amounts of vitamins, minerals, and fiber, which can help to lower cholesterol and enact anti-atherogenic activity [24]. Rice by-products are richer in nutrients when compared to polished rice [3]. Rice bran has been seen to provide nutrition and received high attention whereas other rice byproducts have applications in agriculture. Importantly, Rice Husk is mainly considered as burning waste to recover energy. In other fields like animal feed, Rice Husk has limited value due to its low digestibility and bulk density. They are also used in cosmetics, construction materials, and as food additives [20].

- 1) *Rice Husk*: Rice Husk is a major by-product obtained by the rice milling process [25]. These are the protective coverings of rice grains [26] protecting them from physical damage and attacks by pathogens, insects, and pests in the paddy plant before milling [27]. Annually, around 12 million tons and 80 million tons of Rice Husks are produced in India [28] and worldwide respectively [29]. Rice Husks have an irregular boat-like shape [30] with a hard surface [31]. It is very lightweight, having a packing density of 122 kg/m³ [30] with high silicon content, and thus difficult to get decomposed by bacteria [5]. The main elemental components of Rice Husk are C- 37.05 wt.%, H- 8.80 wt.%, N- 11.06 wt.%, Si- 9.01 wt.% and O- 35.03 wt.% [31]. Rice Husk biomass is comprised of three polymers, i.e., cellulose (35%) hemicelluloses 15% and lignin (16%), and ash (20%) together with a small amount of starch (up to 7%) [32], [21]. It is considered as cheapest biomass in all lignocellulosic biomasses. Organic substances like cellulose and lignin make up 75-90 % of Rice Husk, while mineral components like silica, alkalis, and trace elements make up the balance [32]. It is a crop by-product having uniform size and high ash content of about (14–25%) [33].

D. Management of Rice By-Products

Rice milling waste is not hazardous waste, but its management is very important due to its larger volume of waste [39]. Only a little portion of Rice Husk produced is utilized consciously out of that large proportion of agro-industrial waste worldwide [40]. Rice Husk has a high level of fiber and low protein and energy which makes it a little difficult to convert it to a value-added product. More reasons hinder its use like lack of awareness, less understanding of technology, economic problem, etc. [41]. So, there is a need for the identification of major opportunities for using and increasing the value of the waste [41] and reducing the cost of waste treatment [32] with both qualitative and quantitative points of view [40].

Sustainable development is crucial these days. The "triple bottom line" approach can help achieve sustainability. This makes sure that environmental, economic, and social aspects are considered altogether with equal importance. This helps to identify the consequences of activities' impacts on all environmental, economic, and social aspects, in turn, taking actions to build a sustainable society [42].

Agricultural wastes are generally the byproducts that are not seen from a utilization point of view and even are of the very huge sector. To solve this problem, these byproducts are being subjected to many pieces of research to make them useful which created many value-added products from the generated waste which is mentioned in this review.

II. BIOADSORBENT

Due to industrialization, wastes are generated in water bodies in huge amounts which affects aquatic life, agricultural products and so human health [43]. The main sources that generate waste are:

- 1) Elemental waste is generated from industries based on metal plating, mining, tanneries, painting, car radiator manufacturing [44], printing and photographic, smelting, batteries, paper, painting, petroleum refining [43] as well as agricultural industries where fertilizer and fungicidal spray, pesticides are excessively used to protect agricultural products [44]. Elements like Cu, Zn, Cr, Cd, Ni, Co, Pb, Hg, As, etc. are harmfully non-biodegradable wastes thus get accumulated and contaminate groundwater and other natural wastes streams [44], [43] where it is usually discharged [45].
- 2) The dyes as a major waste products are discharged into water bodies from industries based on textiles, rubber, paper, plastics, cosmetics, etc., to color their products which are hazardous and may pollute the environment, aquatic life, and different food chains [44].
- 3) Other than these wastes, there are some generalized organic pollutants disposals causing water toxicity like phenolic and polycyclic hydrocarbons, pesticides and herbicides, fertilizers, biphenyls, detergents, greases, oils, and pharmaceutical compounds. These are mutagens and carcinogens which accumulate in the environment affecting health [49], [50].

A. Strategies Toward Clean Water Bodies

As these pollutants need to be ceased before they stream into water bodies are gaining a lot of concerns these days. There are a few strategies (layer filtration, coagulation, adsorption, oxidation, particle trade, precipitation, ion exchange, carbon adsorption [51] biodegradation, oxidation, ion exchange, precipitation, adsorption, coagulation, flocculation, filtration, irradiation, electro dialysis, reverse osmosis, membrane process, ozonation, distillation and solvent extraction [43] accessible for the expulsion of all the pollutants from wastewaters. However, only some of them were used on account of their minimal expense, high effectiveness, appropriateness to a wide variety of toxins, and low maintenance costs [46]. Thus highly economical alternate technologies or sorbents for the treatment of metal-contaminated waste streams were needed.

Sorption could be an extremely effective procedure because of low money investment, easy handling and operation, rapidity, and accessibility of various adsorbents without the formation of toxic substances. [52], [53], [54]. An adsorbent ought to have many characteristics like accessibility, non-toxicity, affordable, high surface capability, high abrasion resistance, and environmentally stable [49], [55]. The adsorption process is affected by many experimental parameters such as contact time, initial concentration, pH, particle size, agitation rate, competitive ions (2055 R), the effect of temperature [46], agitation time, sorbent dosage [45], flow rate and characteristics of the column in continuous operation [43], the effect of modifications/treatments [57].

B. Other Wastes as Bioadsorbents

A kind of suitable adsorbent is Rice Husk which is readily available at low cost and has been proved to be a good sorbent over others. However, there are many more biomaterials that are being used for the adsorption technique to remove unwanted dyes and metals from water resources such as cashew nutshell [56], apple pomace [58], banana peel, orange peel, peanut hull [59], Indian rosewood [60], wheat shells [61], hazelnut shells, cherry tree [62], eucalyptus bark, Rubber dddd sawdust, black gram husk, Waste tea leaves, Papaya wood, Powder of green coconut shell, jack fruits, Neem leaf powder [63]wheat straw [64], soy meal hull [65], grapefruit peel [66], banana stalk [67], sugarcane bagasse [68], coconut shell [69]which have good efficiency to adsorb different adsorbates. To date to make the adsorbents highly effective, by increasing the surface area of the adsorbent in the pretreatment step there are many modifying agents have been used such as NaOH, HNO₃ [59], Formaldehyde, sulphuric acid [60], Citric acid [64], H₃PO₄, ZnCl₂ [70], potassium hydroxide (KOH) and carbon dioxide [67], HCl [68].

For Rice Husk Epichlorohydrin, Tartaric acid, 4M N-(3-chloro-2- hydroxypropyl) trimethylammonium chloride, Orthophosphoric acid, and Polyaniline are the modifying agents [71].

C. Rice Husk as Bioadsorbents

Rice Husk is used as a sorbent in removing heavy metals and dyes and has been intensively studied and reported. There are much value-added modifications done to Rice Husk to make it work as sorbent. These modifications produced many kinds of adsorbents as a product such as:

Zeolites [72], biochar [73], silica gels, pretreated powder, activated carbon, Silica Activated Carbon Composite, Rice Husk ash, etc. Adsorption properties of Rice Husk have been studied because of its low price and richness in silica [74].

There are many metals on which studies are carried out like: As(V), Cd, Co, Cr (III), Cr(VI), Cu, Hg, Ni, Pb and Zn [44], Cu, Pb(II), Zn(II), Ni(II) [43], selenium [75]. [76] showed that the amount of Pb ions adsorbed per unit mass of Rice Husk is more than the other ions with this trend: Pb > Hg > Cd > Cu > Co > Mn > Zn > Ni. [77] Showed Pb adsorption was higher than Hg (10.86 and 3.23 mg/g, respectively). [114] showed that metallic ion adsorption by activated carbon with maximum adsorption in the order Cd(II) > Cu(II) > Zn(II) > Hg(II).

The maximum adsorption capacity for each metal ion from previous works has been summarized in table:1. The values of referenced adsorption capacity should be considered as values under explicit conditions but not as maximal adsorption limits [44]. Table:1 shows that the adsorption of metal Pb is more effective than for other metals by Rice Husk modified adsorbents.

Table-I
The adsorption capacity for metal ion

S.no.	Adsorbate	Capacity (mg/g)	Reference
1.	As(V)	615.11	[78]
2.	Co (II)	0.32	[79]
3.	Cr (III)	1.90	[79]
4.	Cr (VI)	164.31	[78]
5.	Hg	66.66	[80]
6.	Zn	30.80	[81]
7.	Cu	31.85	[82]
8.	Pb	120.48	[83]
9.	Zn(II)	35.3	[84]
10.	Ni(II)	26.6	[85]
11.	Ar(V)	90.7%	[86]
12.	Cu(II)	112.43	[87]
13.	Pb(II)	207.50	[88]
14.	Cd(II)	164.31	[89]
15.	As(III)	1.22	[90]
16.	Se(IV)	40.92	[75]

Table:2 shows some of the dyes that have been effectively removed by the Rice Husk or modified Rice Husk made bioadsorbant. It is clearly showing that Rice Husk has the highest capacity for adsorbing two dyes that are safranin and methylene blue.

[91] Shown order of effectiveness of adsorption process by various treatments Glutradehyde < methanol < ethanol < NaOH < NH₄OH < boiling < native < Triton X- 100 < heat treated < CTAB < MgSO₄ < CaCl₂.H₂O < NaCl < HNO₃ < H₂SO₄ < HCl. Boiling of Rice Husk showed zero effect on the biosorption capacity of the biomass. [92] Shown enhancement of sorption capacity after modification of biomass with HCl, H₂SO₄, and HNO₃ acids.

Table-II
Adsorption Capacity for Dyes

S.no.	Adsorbate	Capacity (mg/g)	Reference
1.	Acid yellow 36	86.9	[93]
2.	Methylene Blue	1450-1950	[94]
3.	Indigo carmine	4.86 (95%)	[95]
4.	Crystal Violet	44.87	[96]
5.	Acid yellow 17	12.98 (97.97%)	[97]
6.	Basic Green 4	511	[98]
7.	Basic Red 2	838	[99]
8.	Basic Blue 9	312	[99]
9.	Safranin	838.00	[99]
10.	Direct Orange-26	19.96	[100]

There are many other organic compounds that have been studied for their adsorption capacity by Rice Husk such as: ammonium [73], phenol [101], humic acid [102], pyridine [103], alpha picoline [104], Dibenzothiophenes in kerosens [105], Naphthalene, Phenanthrene [106], 2,4-dichlorophenoxyacetic acid [107], Catechol, Resorcinol [108], NH_4Cl , slurry solution [109].

[110] depicted the adsorption in dairy wastewater using Rice Husk. In this example, the phenomena of adsorption were favored by a lower temperature and pH. Maximum removal as high as 92.5% could be achieved using an adsorbent dosage of 5 gm/L, pH of 2, and temperature of 30°C. In [111] Rice Husk is also being used as ash to produce Thiol modified magMCM-41 nanoparticles for the adsorption of herbicides 2,4-D and glyphosate showing adsorption efficiency between 60-70% with different optimized factors like pH, temperature, contact time, etc. In [72] Rice Husk and waste aluminum cans were used as silicon and aluminum sources, respectively for the synthesis of some nanosized zeolite, zeolite/zeolite, and geopolymer /zeolite products for the removal of Co(II), Cu(II), and Zn(II) ions from aqueous media and show its cost-effectiveness. Rice Husk powder was found to be better than acid-treated Rice Husk powder in [112], [113], where it was employed as a cheap efficient bioadsorbent for defluoridation of water. In [115] Rice Husk was coated with aluminum to make it a better adsorbent for the removal of fluoride from drinking water. According to the research, the method can remove up to 10 mg/g of fluoride. The other end products from Rice Husk that can be used to develop bioadsorbents are depicted in Fig. 1

III. BIOFERTILIZERS

Agriculture is a prominent practice that rules the economy in developing countries [116]. Presently, soil and agriculture management strategies are mainly dependent on continuous high usage of agrochemicals such as chemical fertilizers, pesticides, and water, with the increasing use of extracting machines to gain maximum output in less time is a great achievement for agricultural industries [117], [118]. However, excessive use of chemical fertilizers, composts, and pesticides is not only of high cost but also a thing of environmental threat [118]. Chemical fertilizers cause air and groundwater pollution by an increase in the concentration of P, N, and other excess plant nutrients in water bodies that deteriorate the water quality and the depletion of dissolved oxygen [119]. Chemical fertilizers also deteriorate soil ecology, degrade soil fertility and show harmful effects on human health [120].

Therefore, naturally occurring biofertilizers and composts could be a good alternative to chemical fertilizer which enhances nutrient rotation and the biodegradation process using microorganisms [121]. Biofertilizers are accepted as inputs for organic agriculture by the International Federation of Organic Agriculture Movements (IFOAM, 2005). The quality of the carrier is a vital factor in determining the microbial load and shelf life of biofertilizers [122]. Currently, Rice Husk is used as a bulking agent for composting [123] and carrier materials for biofertilizers [122]. Different carriers have been used such as Rice Husk ash, vermiculite, peat, wheat bran, alginate, and clay which are regarded as good materials for use as a carrier [124].

A. Microbes for Biofertilizers

Biofertilizers contain living organisms that colonize the rhizosphere of the plant and act as stimuli for plant growth by increasing the availability of primary nutrients [125]. Plant Growth Promoting Rhizobacteria (PGPR) is the group of many soil bacterial species on which many commercial biofertilizers are based [117], [121]. On the basis of bacterial species, there are 4 types of biofertilizers like Nitrogen fixing biofertilizers, Phosphorous solubilizing biofertilizers (PSB), Phosphate mobilizing biofertilizers, and Plant growth-promoting biofertilizers. Microorganisms like: *Rhizobium*, *Azospirillum*, *Azotobacter* (N_2 fixing bacteria), *Bacillus*, *Pseudomonas*, and *Aspergillus* (P-solubilizer), *Mycorrhiza* (phosphate mobilizers), *Pseudomonas* sp. (Plant growth promoter) [117]. According to reports, Organic farming increases soil composition, fertility, and soil fauna, all of which benefit crop productivity in the long run [116]. [123] observed that composter Rice Husk resulted in significant increases in Ca, Mg, Si, K, and Na concentrations of the in situ soil solution compared to the control treatment and the concentrations of Al, Mn, Fe, and Zn (as toxic elements for crop growth if present in excess amounts) significantly decreased.

[131] depicted the change in the growth of Soursop (*Annona muricata* L.) in the presence of Rice Husk Biochar (RHB) and compared it with growth in the presence of arbuscular mycorrhizal fungi (AMF). It was observed RHB, either individually or in combination with AMF, had significantly improved the growth performance of soursop seedlings at the nursery stage indicated by a significant increase in shoot and root biomass, root length, root surface, area, and leaf area meter. [132] determined the potential of some biochar as a carrier of biological fertilizer for swamplands. It was estimated the better quality of carrier material of different microbes. Biochar Rice Husks, are very effective as *Trichoderma*, *Bacillus*, and *Azotobacter*. Thus, Rice Husk biochar can be used as a carrier material as a single biofertilizer, as well as a consortium biofertilizer consisting of decomposer fungi, P solubilizing bacteria, and N-fixing bacteria.

[122] experimented over moisture content, bulk density, porosity and water absorption capacity, and pH of Rice Husk and cassava peel. Both carrier materials also supported the growth of the test organism which suggested the presence of nutrients and absence of toxicity. The molds in cassava peel became infected after 2 weeks while biofertilizer produced with Rice Husk, even after drying, remained viable for more than six weeks due to high silica (SiO_2) content, of about 19 % in Rice Husk which makes it less susceptible to microbial attack and therefore easier to preserve. Thus, Rice Husk has a higher shelf life to be used as biofertilizers. In [136] shown Rice Husk charcoal can operate as an adsorbent of organic chemicals such as fertilizers and insecticides, as demonstrated by its 38 mg g^{-1} Methylene blue adsorption capability. This allows for a slow-release effect on fertilizers for crop absorption, as well as a reduction in pesticide pollution.

Rice Husk ash was suggested as a superior carrier for supporting microorganisms in the bio-fertilizer process while also improving soil structure [121]. The treatment comprising Rice Husk ash as a carrier, combined with rhizobacteria in saline soil had the highest overall enzyme activity as measured by the fluorescein diacetate hydrolysis (FDA) technique. Rice Husk ash is a good source of carbon and silica, and the porous structure is helpful for microbes and moisture retention. This means that the plant can absorb silicon in a soluble form through its roots [137]. When opposed to using cell suspension directly into the soil, bacteria survive longer when immobilized in the carrier. Microorganisms can proliferate and survive for lengthy periods of time in these carriers [124]. Rice Husk ash also helps to improve soil structure by enhancing soil porosity, aeration, and moisture retention. As a result, using Rice Husk ash as a carrier proved successful in raising the soil microbe population and, as a result, plant development.

IV. BIOINSULATORS

Insulation is defined as the act of preventing heat, electricity, or sound from flowing or passing through a material, medium, or system [138]. Buildings consume most of the energy used for air conditioning in all seasons [139], especially in summer and winter, unless the roof and walls are well insulated. In buildings or any other thermal application, thermal insulation is a very important way to conserve energy. For buildings, insulation can reduce the rate of heat transfer between the air-conditioned area and its surrounding environment that is, reducing heat transfer between two zones having different temperatures [140] to maintain a certain temperature in any environment. In such circumstances, thermal conductivity is employed exclusively, so evaluating the thermal conductivity of the selected materials can aid in determining whether or not they can be used for thermal insulation purposes [138].

A. Characteristics of Insulators

Some of the basic properties which are generally considered for designing insulators are thermal property, absorption, hardness, and combustion, [141] i.e. low thermal conductivity, moisture protection, resistance to mold growth and insects [142] and non-flammability, non-toxicity, and higher strength [143], lightweight and good recycling characteristics, less costly. [140] as well as considered to be environment and human health friendly since today's popular inorganic insulation materials have a negative impact from the production stage to the end of their useful life. [141], [144]. Dielectric property and reliability are also the most important characteristics of any insulator [145].

B. Harmful Effects of Insulators on Environmental

Thermal insulating materials such as fiberglass, rock wool, mineral wool, polystyrene, polyurethane foam, and cellulose are extensively utilized, however they are detrimental to the environment [140]. The majority of thermal insulation baths include formaldehyde resins which can trigger asthma attacks [147]. Small particles from fiberglass and glass wool insulation can be harmful to one's health and respiratory system or skin irritation. [148] The use of hazardous, fire-retarding compounds like boric acid in cellulose insulation has been identified as having the potential to have significant health consequences [149]. Vice versa if we consider, that renewable fiber thermal insulation derived from trees, plants, or animals has the potential to regenerate itself, uses less energy to manufacture, and degrades quickly when discarded, resulting in a low environmental effect [150]. Thus, the majority of recent studies have concentrated on agricultural waste products, while others have looked into industrial waste materials, and only a few have looked into animal waste materials [140].

Coconut and sugarcane fiber, cotton, wheat straw, palm leaves, and oil palm fiber [151], coconut husk, maize cob or stalk oil palm shell, and leaves or straw from cereal crops with high fiber content [142], sugarcane bagasse [152], miscanthus fiber, sunflower stalk fiber [153], stubble fibers [154], food crop by-products [155], rice straw [156] [157], Rice Husk [158], wood fibers/textile fibers [159], coffee chaff [160], and corn stalk [161]. All of these materials can be used as the major component of composite materials, making them appropriate for the production of boards and panels [142].

Silica has an extremely low thermal conductivity of about 0.01–0.03 W/m.K. Biological silica comes from natural ash. Insulation using bio-silica has been carried out in the production of cordierite and forsterite and for extruded and pressed insulation [162]. Recent research has begun on insulators for construction utilizing RHA as a silica source [163]. Rice Husk products are poor in nutrients, have high wear strength, and contain a lot of ash. Ash has a very high quantity of silica ranging from 80% to 95%. The burning of Rice Husk produces different types of ashes based on the different process parameters used during husk burning. These ashes have different functions based on varied chemical, mineralogical and morphological characteristics [164] in husks burned below 70°C, amorphous silica predominates, whereas crystalline silica predominates in husks burned above 70°C [165]. Silica in ashes makes them have low thermal conductivity and mechanical characteristics, resistant to chemical etching (acid slag) and thermal shock (temperature changes above 60°C). Because of the greater residual carbon content, coarse grains, presence of oxides, and poor crystallinity which helps to achieve low thermal conductivity, amorphous silica is useful in ceramic thermal insulators. As a result of these qualities, they could be employed as raw materials in industrial ceramic processes like thermal insulation [166].

C. Properties of Rice Husk Ash for Insulators

The following are some of the benefits of using RH ash: (i) it is obtained in very fine powder form, which saves energy for size reduction; (ii) it is relatively more reactive due to its amorphous nature and large surface area, which is expected to reduce the formation as well as sintering temperature of forsterite ceramics; and (iii) it is an agricultural waste, which reduces the cost of production [167].

There are certain materials that are used as additives to produce a usable and commercial insulator such as:

- 1) Plasticizers are added to provide viscosity and elasticity to the ceramic paste making the particles cohesive and aiding their flow during forming insulators as ashes lack the property of plasticity. Eg. Polysaccharide PS1, and polyvinyl alcohol (PVA). During the sintering process these additives are removed thus, don't hinder the final product chemically.
- 2) Pores-causing substances are used to increase the final porosity. The amount of substance is experimentally determined, in such a way that during forming and sintering laminating effect can be avoided. Eg. Wood sawdust.
- 3) Flux is added to support pore formation by absorbing water and swelling itself. On humidification, it becomes plastic which aided increased workability and formation of the ceramic paste. Eg. Bentonite. Its presence in the ceramic paste is beneficial [166].

[145] has examined for the dielectric value of a pressboard, that's used inside the transformer, and was covered with 3 components: epoxy resin, Rice Husk ash, and quartz powder. Quartz powder and Rice Husk ash were combined in a specific ratio with the epoxy resin. The dielectric constant of the covered pressboard is 3.273 at 1 kV and volume resistivity is likewise excessive at $3.18 \times 10^{13} \Omega \cdot \text{cm}$ at 500V DC supply for the covered pressboard which was better than the non-coated press board (2.650 at 1 kV). [169] used a biodegradable poly (butylene adipate-co-terephthalate)/poly (lactic acid) (PBAT/PLA) blend binder and four different types of locally available by-products (Rice Husk, wheat husk, wood fibers, and textile waste fibers), composites were made by hot pressing. The Rice Husk composite with a density of 378 kg/m³ had the lowest thermal conductivity, 0.08 W/m.K. After 24 hours of immersion in water, the Rice Husk composites had a minimum water absorption of 42%. By replacing traditional building materials with the created biocomposites, the environmental effect will be reduced.

[163] organized and integrated ash (RHA) and RHA-derived silica aerogel as a filler (0-10%) into low-density polyethylene (LDPE) resulting in a composite where the overall performance of each filler had been compared. Thermal stability of both the composites with fillers was being upgraded as compared to unfilled LDPE however among the silica aerogel and RHA filler's composites, silica aerogel had a better performance than RHA as filler in the composites. Silica aerogel as filler indicated thermal insulation strength with 0.0926-0.1820 W/m.K as compared to RHA at 0.3275-0.3532 W/m.K and unfilled LDPE samples at 0.3889 W/m.K. Both fillers showed better thermal stability however the addition of silica aerogel as a filler (2-10%) indicated higher thermal stability and thermal conductivity than RHA.

[171] determined the thermal conductivity for a mixture of Rice Husk fiber and gypsum and 100% gypsum. Four samples have been tested with different ratios of gypsum and Rice Husk. The evaluation resulted in a decrement in thermal conductivity with the increment of Rice Husk fiber in the sample. The value of thermal conductivity of the sample having less ratio of Rice Husk is 0.772W/mK whereas the sample with a high ratio of Rice Husk had 0.7368W/mK. Rice Husk shows thermal properties of insulator when mixed with gypsum and thus could be used as plaster ingredient and ceiling finishing.

In [138] the mixture of Rice Husk and Plaster of Paris was evaluated as insulation materials. The addition of 1% Rice Husk has proven a minor impact on the insulation properties of Plaster of Paris, 3% of Rice Husk gave higher insulating properties and proven to be the best combination of insulating properties, strength, and porosity.

Whereas 5% concentration of Rice Husk increased the porosity of the structure and allowed more heat to flow thus the thermal conductivity recorded was higher.

The effects revealed that the addition of Rice Husk to the mixture to just a concentration would display better thermal insulation and after exceeding quantity might increase porosity in turn increasing thermal conductivity. In [142] the potential for using Rice Husk, Bagasse, and Corncob composite samples as thermal insulation materials have been investigated.

According to the findings of the assessments, sample G with $0.231\text{Wm}^{-1}\text{k}^{-1}$ of thermal conductivity and 22.114m^{-1} of specific heat was the best combination with 60% of Rice Husk and a significant proportion of bagasse to a smaller percentage of the corncob. The overall assessment shows the commendable insulation property of Rice Husk as well as increased insulation property of insulators when mixed with Rice Husk.

V. HYDROPHOBIC COATINGS

Superhydrophobic surfaces (water repellent/ weatherproof surfaces) [173] are in great demand in recent years as per their requirement in different industries such as automobiles and medical industries, etc. [174]. Most importantly these can be used in the field of construction as penetration of water into concrete does more than just cause destruction by expanding, but also allows the invasion of corrosive chloride ions. Therefore, hydrophilic concrete production needs to be stopped to prevent deterioration and structural damage to concrete. Different types of water-resistant materials can be used to reduce the wetting of concrete [175].

A. Properties of Superhydrophobic Surface

Various research works have been carried out to create a superhydrophobic surface. The idea of adding additional properties of different sectors such as anti-corrosion, anti-icing, anti-fogging, self-cleaning, and anti-fouling, to the superhydrophobic coatings which have unique structure [174] to combat the adverse weather conditions [175].

Hydrophobicity of a surface is based on the principle of the angle between the water droplet and the surface. The greater the angle between them greater will be the hydrophobicity. Superhydrophilic, hydrophilic, hydrophobic, and superhydrophobic water contact angles (WCA) vary from 0° to 10° , 10° to 90° , 90° to 150° , and 150° to 180° , respectively. In superhydrophobic coatings, water droplets easily roll down from their surface [174].

Superhydrophobic coatings can either be generated by grafting hydrophobic groups including CH_3 , CH_2CH_2 , and CF_3 [176] or hydrophobic chemicals can be used including silane, siloxanes, and silicones [177] on the substrate to reduce the surface energy of concrete [176]. These silicon-based chemicals contain hydrophobic alkyl groups to prevent wetting [175]. To modify the substrate surface ultra-violet technique, photo-polymerization and spray technique [174] lithography techniques, phase inversion, surface etching, sol-gel method [178, 179] self-assembly [180], templating [181], chemical etching [182], electrospinning [183] and chemical vapor deposition [184] which have been reported.

Besides these, nanoparticles (such as nano-silica, titanium dioxide, zinc oxide, etc) [174] can be added to the substrate to generate the required roughness [176] affecting its morphology at the nanoscale dimension 35 for the production of superhydrophobic coating. It is time-saving and affordable and even there is no requirement for expensive equipment or rigorous conditions. [175]. As a result, the most common superhydrophobic coating formulation is made up of a hydrophobic polymer and inorganic nanoparticles distributed in a solvent. Various types of hydrophobic polymers were studied in the development of superhydrophobic coatings [187].

Matrix material for fabricating superhydrophobic coatings should have features like flexibility, good processability and low costs. These polymers generally have different structural and functional groups with suitable branches that are interconnected using the covalent bond to produce different configurations to use it where low adhesion and low friction are needed.

These materials can fulfill the need in the fields where self-cleaning, self-healing, anti-icing, anti-adhesion, and oil/water separation applications are required. The factors including nanoscale roughness, surface energy, coating thickness, mechanical stability, and bonding strength between the substrate and coating are responsible for attaining a superhydrophobic surface. [185, 186] Roughness in the micro and nanometer scale and a coating of low surface energy are the two essential requirements that needed to be met in order to create a superhydrophobic surface [188].

B. Rice Husk for Superhydrophobic Coatings

Due to silica as a Rice Husk constituent, it can suitably replace costly commercial nanoparticles. The ash should consist of amorphous silica instead of crystalline silica when used as a superhydrophobic coating [189] as it is used to create the roughness required by the superhydrophobic coating on concrete.

The high strength and comparatively low cost of nano-silica powders make them suitable for their use. If these silica powders can be extracted from waste products, then it would minimize the further costs. It would also help in controlling waste disposal and other related problems. Rice Husk is one such waste product available in abundance in Asian countries. Disposal of paddy and the left ash from burning is a major issue in many developing countries. [190]

Many types of research have been done in order to produce the best hydrophobic coatings made from biowastes. Junaidi et al. created a superhydrophobic covering made of Rice Husk ash and silica with photoluminescence characteristics (RHA). The RHA was calcined at 550 and 650 degrees Celsius to produce silica particles with a negligible quantity of carbon residual in this study. To make superhydrophobic coatings, the RHA-SiO₂ was chemically treated using 1H,1H,2H, and 2H perfluorodecyltriethoxysilane (HFDS). The water contact angle of the covered concrete was 157.7° [191].

Rice Husk ash was mixed in an ethanolic solution containing fluoroalkyl silane, 1H, 1H, 2H, and 2H-perfluorodecyl triethoxy silane to make the superhydrophobic coating (2 vol. percent). The ash solution was sprayed on top of a commercial adhesive coating that had been applied to the concrete. On the covered concrete, a water contact angle of 152.3 0.5 was measured. The total amount of water taken in was lowered by 40.38 percent, and the water sorptivity was reduced by 44.44 percent. Water penetration into the covered concrete was successfully decreased after 72 hours at 500 kPa water pressure, but not completely avoided [192].

Husni et al., sprayed the ash solution on top of a commercial adhesive primer layer that had been applied to the concrete. Water penetration into the covered concrete was reduced after 72 hours of testing under a water pressure of 500 kPa, but not totally avoided [195]. Overall, it is suggested that silica particles in Rice Husk ash may be employed to generate superhydrophobic concrete coatings. Rice Husk ash was disseminated in ethanol containing 1H,1H,2H, and 2H-perfluorodecyltriethoxysilane to make these coatings.




Fig. 1. End products made from Rice Husk which is used as effective adsorbents.

VI. CONCLUSIONS

The use of Rice Husk which is easily available and of low cost could solve the problem of its disposal while also lowering the cost of waste management. Rice Husk and ash are directly used in the production and synthesis of new materials.

One of the most researched products is a bio adsorbent made from Rice Husk that has a great capacity for adsorbing heavy metals and dye in various water bodies. By treating it with various chemicals, the adsorbing capability can be improved. Until now, Rice Husk bioadsorbent has been most effective in adsorbing methylene blue and As (V). Second, biofertilizers are an excellent alternative to chemical fertilizers since they enhance important elements in the soil while lowering hazardous elements. As a strong supplier of silica and carbon, it provides a good carrier for microbes and plants to flourish, extending their shelf life.

Then there are bioinsulators manufactured from Rice Husk, which have been considered because of their unique features and lowest thermal conductivity among all the other materials used to make bioinsulators, owing to a large amount of silica (80-95 %) in them. The use of Rice Husk reduces the overall thermal conductivity of composites when combined with other materials.

Finally, because of the increased silica content, Rice Husk is employed to create adequate roughness in order to make a superhydrophobic covering. This coating is primarily created by spraying a Rice Husk solution onto adhesive coatings, resulting in a higher quality finish. All four products were thoroughly examined, and it was determined that Rice Husk may be a better choice in many applications than other waste products, and that various improvements could be made to improve it. The various benefits of Rice Husk and Rice Husk ash can be realized through future vital research efforts, giving new energy for local and regional sustainable development.

Apart from enriching the properties of the products and launching value-added products, the Rice Husk is used to produce new products like biofuels, and bioenergy after subjecting it to microbial fermentation which is a major field of future research and studies in Science and Engineering.

REFERENCES

- [1] Jittin, V., A. Bahurudeen, and S. D. Ajinkya. "Utilisation of Rice Husk ash for cleaner production of different construction products." *Journal of cleaner production* 263 (2020): 121578.
- [2] Kumar, Anuj, et al. "Recovery of value added products from Rice Husk ash to explore an economic way for recycle and reuse of agricultural waste." *Reviews in Environmental Science and Bio/Technology* 15.1 (2016): 47-65.
- [3] Esa, Norhaizan Mohd, Tan Bee Ling, and Loh Su Peng. "By-products of rice processing: An overview of health benefits and applications." *Rice Research: Open Access* (2013).
- [4] Frei, Michael, and Klaus Becker. "On rice, biodiversity & nutrients." Univ of Hohenheim, Stuttgart. Available online: [http://www. greenpeaceweb.org/gmo/nutrients.\(2004\)](http://www.greenpeaceweb.org/gmo/nutrients.(2004)).
- [5] FAO. 2021. Crop Prospects and Food Situation - Quarterly Global Report No. 1, March 2021. Rome.
- [6] Shukla, Neha, Diptiprakash Sahoo, and Neelancherry Remya. "Biochar from microwave pyrolysis of Rice Husk for tertiary wastewater treatment and soil nourishment." *Journal of Cleaner Production* 235 (2019): 1073-1079.
- [7] Carmona, V. B., et al. "Nanosilica from Rice Husk: extraction and characterization." *Industrial Crops and Products* 43 (2013): 291-296.
- [8] Lim, Jeng Shiun, et al. "A review on utilisation of biomass from rice industry as a source of renewable energy." *Renewable and sustainable energy reviews* 16.5 (2012): 3084-3094.
- [9] Khush, Gurdev S. "Origin, dispersal, cultivation and variation of rice." *Plant molecular biology* 35.1 (1997): 25-34.
- [10] Itoh, Jun-Ichi, et al. "Rice plant development: from zygote to spikelet." *Plant and cell physiology* 46.1 (2005): 23-47.
- [11] Umadevi, M., et al. "Rice-traditional medicinal plant in India." *Journal of pharmacognosy and phytochemistry* 1.1 (2012): 6-12.
- [12] Dhankhar, Poonam, and T. Hissar. "Rice milling." *IOSR J Eng* 4.5 (2014): 34-42.
- [13] Nambi, V. Eyarkai, Annamalai Manickavasagan, and S. Shahir. "Rice milling technology to produce brown rice." *Brown Rice*. Springer, Cham, 2017. 3-21.
- [14] Koopmans, Auke, and Jaap Koppejan. "Agricultural and forest residues-generation, utilization and availability." *Regional consultation on modern applications of biomass energy* 6 (1997): 10.
- [15] Bodie, Aaron R., et al. "Current trends of rice milling byproducts for agricultural applications and alternative food production systems." *Frontiers in Sustainable Food Systems* 3 (2019): 47.
- [16] Alizadeh, Mohammad Reza. "Effect of paddy husked ratio on rice breakage and whiteness during milling process." *Australian journal of crop science* 5.5 (2011): 562-565.
- [17] Akintunde, Mutalubi Aremu. "Development of a rice polishing machine." *Assumption University (AU) Journal of Technology, Thailand*, article 6 (2007): 105-112.
- [18] Autrey, HARRY S., et al. "Rice milling, effects of milling conditions on breakage of rice grains." *Journal of Agricultural and Food Chemistry* 3.7 (1955): 593-599.
- [19] Bao, Jinsong. "Rice milling quality." *Rice*. AACC International Press, 2019. 339-369.
- [20] Bodie, Aaron R., et al. "Current trends of rice milling byproducts for agricultural applications and alternative food production systems." *Frontiers in Sustainable Food Systems* 3 (2019): 47.
- [21] Favaro, Lorenzo, et al. "Production of bioethanol from multiple waste streams of rice milling." *Bioresource Technology* 244 (2017): 151-159.
- [22] Ubwa, Simon Terver, et al. "Studies on urea treated rice milling waste and its application as animal feed." *African Journal of Pure and Applied Chemistry* 8.2 (2014): 23-31.

- [23] Sanchez, Juan, et al. "Growth performance, gastrointestinal weight, microbial metabolites and apparent retention of components in broiler chickens fed up to 11% rice bran in a corn-soybean meal diet without or with a multi-enzyme supplement." *Animal Nutrition* 5.1 (2019): 41-48.
- [24] Wilson, Thomas A., et al. "Whole fat rice bran reduces the development of early aortic atherosclerosis in hypercholesterolemic hamsters compared with wheat bran." *Nutrition Research* 22.11 (2002): 1319-1332.
- [25] Mansaray, K. G., and A. E. Ghaly. "Physical and thermochemical properties of Rice Husk." *Energy sources* 19.9 (1997): 989-1004.
- [26] Singh, Bhupinder. "Rice Husk ash." *Waste and supplementary cementitious materials in concrete*. Woodhead Publishing, 2018. 417-460.
- [27] Zou, Yanping, and Tiankui Yang. "Rice Husk, Rice Husk ash and their applications." *Rice Bran and Rice Bran Oil*. AOCs Press, 2019. 207-246.
- [28] Todkar, Bajirao S., Onkar A. Deorukhkar, and Satyajeet M. Deshmukh. "Extraction of silica from Rice Husk." *International Journal of Engineering Research and Development* 12.3 (2016): 69-74.
- [29] Wu, Jia, et al. "Optimising conditions for bioethanol production from Rice Husk and rice straw: effects of pre-treatment on liquor composition and fermentation inhibitors." *Biotechnology for biofuels* 11.1 (2018): 1-13.
- [30] Fang, M., et al. "Experimental study on Rice Husk combustion in a circulating fluidized bed." *Fuel processing technology* 85.11 (2004): 1273-1282.
- [31] Li, Ying, et al. "A new method of comprehensive utilization of Rice Husk." *Journal of hazardous materials* 186.2-3 (2011): 2151-2156.
- [32] Kumar, S., et al. "Utilization of Rice Husk and their ash: A review." *Res. J. Chem. Env. Sci* 1.5 (2013): 126-129.
- [33] Patil, Ragini, Rajendra Dongre, and Jyotsna Meshram. "Preparation of silica powder from Rice Husk." *Journal of Applied Chemistry* 27 (2014): 26-29.
- [34] Goodman, Bernard A. "Utilization of waste straw and husks from rice production: A review." *Journal of Bioresources and Bioproducts* (2020).
- [35] Kamath, Savita R., and Andrew Proctor. "Silica gel from rice hull ash: preparation and characterization." *Cereal Chemistry* 75.4 (1998): 484-487.
- [36] Mane, Venkat S., Indra Deo Mall, and Vimal Chandra Srivastava. "Kinetic and equilibrium isotherm studies for the adsorptive removal of Brilliant Green dye from aqueous solution by Rice Husk ash." *Journal of environmental management* 84.4 (2007): 390-400.
- [37] Kuan, Chiu-Yin, Kay-Hay Yuen, and Min-Tze Liang. "Physical, chemical and physicochemical characterization of Rice Husk." *British Food Journal* (2012).
- [38] Soltani, N., et al. "Review on the physicochemical treatments of Rice Husk for production of advanced materials." *Chemical engineering journal* 264 (2015): 899-935.
- [39] Ubwa, Simon Terver, et al. "Studies on urea treated rice milling waste and its application as animal feed." *African Journal of Pure and Applied Chemistry* 8.2 (2014): 23-31.
- [40] Giddel, M. R., and A. P. Jivan. "Waste to wealth, potential of Rice Husk in India a literature review." *International conference on cleaner technologies and environmental Management PEC, Pondicherry, India*. Vol. 2. 2007.
- [41] Moraes, Carlos AM, et al. "Review of the rice production cycle: By-products and the main applications focusing on Rice Husk combustion and ash recycling." *Waste Management & Research* 32.11 (2014): 1034-1048.
- [42] Prasara-A, Jittima, and Shabbir H. Gheewala. "Sustainable utilization of Rice Husk ash from power plants: A review." *Journal of Cleaner production* 167 (2017): 1020-1028.
- [43] Shamsollahi, Zahra, and Ali Partovinia. "Recent advances on pollutants removal by Rice Husk as a bio-based adsorbent: A critical review." *Journal of environmental management* 246 (2019): 314-323.
- [44] Chuah, Teong Guan, et al. "Rice Husk as a potentially low-cost biosorbent for heavy metal and dye removal: an overview." *Desalination* 175.3 (2005): 305-316.
- [45] Syuhadah, Noor, and H. Rohasliney. "Rice Husk as biosorbent: a review." *Health and the Environment Journal* 3.1 (2012): 89-95.
- [46] Ahmaruzzaman, M., and Vinod K. Gupta. "Rice Husk and its ash as low-cost adsorbents in water and wastewater treatment." *Industrial & Engineering Chemistry Research* 50.24 (2011): 13589-13613.
- [47] G. McKay, *Am. Dyest. Rep.*, 68 (1979) 29-36.
- [48] McKay, G., V. J. P. Poots, and J. J. Healy. "The Removal of Acid Dye from Effluent Using Natural Adsorbents-I Peat." *Water Res* 10 (1976): 1061-1066.
- [49] Ali, Imran, Mohd Asim, and Tabrez A. Khan. "Low cost adsorbents for the removal of organic pollutants from wastewater." *Journal of environmental management* 113 (2012): 170-183.
- [50] Ngo, Huu Hao, et al. "Typical low cost biosorbents for adsorptive removal of specific organic pollutants from water." *Bioresource technology* 182 (2015): 353-363.
- [51] Bailey, Susan E., et al. "A review of potentially low-cost sorbents for heavy metals." *Water research* 33.11 (1999): 2469-2479.
- [52] Chen, Xue-Gang, et al. "Adsorption of methylene blue by rice hull ash." *Separation Science and Technology* 47.1 (2012): 147-156.
- [53] Crini, Gregorio. "Non-conventional low-cost adsorbents for dye removal: a review." *Bioresource technology* 97.9 (2006): 1061-1085.
- [54] Sharma, Pankaj, et al. "Removal of methylene blue from aqueous waste using Rice Husk and Rice Husk ash." *Desalination* 259.1-3 (2010): 249-257.
- [55] Crini, Gregorio. "Non-conventional low-cost adsorbents for dye removal: a review." *Bioresource technology* 97.9 (2006): 1061-1085.
- [56] Subramaniam, Ramalingam, and Senthil Kumar Ponnusamy. "Novel adsorbent from agricultural waste (cashew NUT shell) for methylene blue dye removal: optimization by response surface methodology." *Water Resources and Industry* 11 (2015): 64-70.
- [57] Safa, Yusra, and Haq Nawaz Bhatti. "Adsorptive removal of direct dyes by low cost Rice Husk: Effect of treatments and modifications." *African Journal of Biotechnology* 10.16 (2011): 3128-3142.
- [58] Robinson, T., B. Chandran, and P. Nigam. "Removal of dyes from a synthetic textile dye effluent by biosorption on apple pomace and wheat straw." *Water research* 36.11 (2002): 2824-2830.
- [59] Annadurai, G., Ruey-Shin Juang, and D. J. Lee. "Adsorption of heavy metals from water using banana and orange peels." *Water science and technology* 47.1 (2003): 185-190.
- [60] Garg, V. K., et al. "Adsorption of chromium from aqueous solution on treated sawdust." *Bioresource technology* 92.1 (2004): 79-81.
- [61] Bulut, Yasemin, and Haluk Aydın. "A kinetics and thermodynamics study of methylene blue adsorption on wheat shells." *Desalination* 194.1-3 (2006): 259-267.
- [62] Ferrero, Franco. "Dye removal by low cost adsorbents: hazelnut shells in comparison with wood sawdust." *Journal of hazardous materials* 142.1-2 (2007): 144-152

- [63] Sud, Dhiraj, Garima Mahajan, and M. P. Kaur. "Agricultural waste material as potential adsorbent for sequestering heavy metal ions from aqueous solutions—A review." *Bioresource technology* 99.14 (2008): 6017-6027.
- [64] Gong, Renmin, et al. "Adsorption behavior of cationic dyes on citric acid esterifying wheat straw: kinetic and thermodynamic profile." *Desalination* 230.1-3 (2008): 220-228.
- [65] Arami, Mokhtar, et al. "Equilibrium and kinetics studies for the adsorption of direct and acid dyes from aqueous solution by soy meal hull." *Journal of Hazardous Materials* 135.1-3 (2006): 171-179.
- [66] Saeed, Asma, Mehwish Sharif, and Muhammad Iqbal. "Application potential of grapefruit peel as dye sorbent: kinetics, equilibrium and mechanism of crystal violet adsorption." *Journal of hazardous materials* 179.1-3 (2010): 564-572.
- [67] Salman, J. M., V. O. Njoku, and B. H. Hameed. "Adsorption of pesticides from aqueous solution onto banana stalk activated carbon." *Chemical engineering journal* 174.1 (2011): 41-48.
- [68] Sadaf, Sana, et al. "Removal of Indosol Turquoise FBL dye from aqueous solution by bagasse, a low cost agricultural waste: batch and column study." *Desalination and Water treatment* 52.1-3 (2014): 184-198.
- [69] Zhu, Yiyang, and Praveen Kolar. "Investigation of adsorption of p-cresol on coconut shell-derived activated carbon." *Journal of the Taiwan Institute of Chemical Engineers* 68 (2016): 138-146.
- [70] Amin, Nevine Kamal. "Removal of reactive dye from aqueous solutions by adsorption onto activated carbons prepared from sugarcane bagasse pith." *Desalination* 223.1-3 (2008): 152-161.
- [71] Lata, Sneha, and S. R. Samadder. "Removal of heavy metals using Rice Husk: a review." *International Journal of Environmental Research and Development* 4.2 (2014): 165-170.
- [72] Abdelrahman, Ehab A., et al. "Utilization of Rice Husk and waste aluminum cans for the synthesis of some nanosized zeolite, zeolite/zeolite, and geopolymer/zeolite products for the efficient removal of Co (II), Cu (II), and Zn (II) ions from aqueous media." *Journal of Hazardous Materials* 401 (2021): 123813.
- [73] Sohaimi, K. S. A., et al. "Ammonium adsorption-desorption using Rice Husk biochar." *IOP Conference Series: Earth and Environmental Science*. Vol. 765. No. 1. IOP Publishing, 2021.
- [74] Soltani, N., et al. "Review on the physicochemical treatments of Rice Husk for production of advanced materials." *Chemical engineering journal* 264 (2015): 899-935.
- [75] El-Shafey, E. I. "Sorption of Cd (II) and Se (IV) from aqueous solution using modified Rice Husk." *Journal of hazardous materials* 147.1-2 (2007): 546-555.
- [76] Krishnani, Kishore K., et al. "Biosorption mechanism of nine different heavy metals onto biomatrix from Rice Husk." *Journal of hazardous materials* 153.3 (2008): 1222-1234.
- [77] Feng, Qingge, et al. "Adsorption of lead and mercury by Rice Husk ash." *Journal of colloid and interface science* 278.1 (2004): 1-8.
- [78] Roy, Dipak, Paul N. Greenlaw, and Barbara S. Shane. "Adsorption of heavy metals by green algae and ground rice hulls." *Journal of Environmental Science & Health Part A* 28.1 (1993): 37-50.
- [79] Marshall, Wayne E., Elaine T. Champagne, and William J. Evans. "Use of rice milling byproducts (hulls & bran) to remove metal ions from aqueous solution." *Journal of Environmental Science & Health Part A* 28.9 (1993): 1977-1992.
- [80] Tiwari, D. P., D. K. Singh, and D. N. Saksena. "Hg (II) adsorption from aqueous solutions using rice-husk ash." *Journal of Environmental Engineering* 121.6 (1995): 479-481.
- [81] Mishra, Shuddhodan P., Diwakar Tiwari, and R. S. Dubey. "The uptake behaviour of rice (Jaya) husk in the removal of Zn (II) ions—A radiotracer study." *Applied radiation and isotopes* 48.7 (1997): 877-882.
- [82] Wong, K. K., et al. "Removal of Cu and Pb from electroplating wastewater using tartaric acid modified Rice Husk." *Process Biochemistry* 39.4 (2003): 437-445.
- [83] Ajmal, Mohammad, et al. "Adsorption studies on Rice Husk: removal and recovery of Cd (II) from wastewater." *Bioresource technology* 86.2 (2003): 147-149.
- [84] Srivastava, Vimal Chandra, Indra Deo Mall, and Indra Mani Mishra. "Characterization of mesoporous Rice Husk ash (RHA) and adsorption kinetics of metal ions from aqueous solution onto RHA." *Journal of hazardous materials* 134.1-3 (2006): 257-267.
- [85] Azadi, Fatemeh, Solmaz Saadat, and Ayoub Karimi-Jashni. "Experimental investigation and modeling of nickel removal from wastewater using modified Rice Husk in continuous reactor by response surface methodology." *Iranian Journal of Science and Technology, Transactions of Civil Engineering* 42.3 (2018): 315-323.
- [86] Asif, Zunaira, and Zhi Chen. "Removal of arsenic from drinking water using Rice Husk." *Applied Water Science* 7.3 (2017): 1449-1458.
- [87] Yahaya, N. K. E. M., et al. "Fixed-bed column study for Cu (II) removal from aqueous solutions using Rice Husk based activated carbon." *Int. J. Eng. Technol* 11.1 (2011): 248-252.
- [88] Naiya, Tarun Kumar, et al. "The sorption of lead (II) ions on Rice Husk ash." *Journal of hazardous materials* 163.2-3 (2009): 1254-1264.
- [89] Roy, Dipak, Paul N. Greenlaw, and Barbara S. Shane. "Adsorption of heavy metals by green algae and ground rice hulls." *Journal of Environmental Science & Health Part A* 28.1 (1993): 37-50.
- [90] Kalderis, Dimitrios, et al. "Adsorption of polluting substances on activated carbons prepared from Rice Husk and sugarcane bagasse." *Chemical engineering journal* 144.1 (2008): 42-50.
- [91] Bhatti, Haq Nawaz, Rabia Khalid, and Muhammad Asif Hanif. "Dynamic biosorption of Zn (II) and Cu (II) using pretreated *Rosa gruss* an teplitz (red rose) distillation sludge." *Chemical Engineering Journal* 148.2-3 (2009): 434-443.
- [92] Yazıcı, Hüseyin, Mehmet Kılıç, and Murat Solak. "Biosorption of copper (II) by *Marrubium globosum* subsp. *globosum* leaves powder: effect of chemical pretreatment." *Journal of Hazardous Materials* 151.2-3 (2008): 669-675.
- [93] Malik, P. Kumar. "Use of activated carbons prepared from sawdust and rice-husk for adsorption of acid dyes: a case study of Acid Yellow 36." *Dyes and pigments* 56.3 (2003): 239-249.
- [94] Vaz, Marcelo G., et al. "Methylene blue adsorption on chitosan-g-poly (acrylic acid)/Rice Husk ash superabsorbent composite: kinetics, equilibrium, and thermodynamics." *Water, Air, & Soil Pollution* 228.1 (2017): 1-13.

- [95] Lakshmi, Uma R., et al. "Rice Husk ash as an effective adsorbent: Evaluation of adsorptive characteristics for Indigo Carmine dye." *Journal of Environmental Management* 90.2 (2009): 710-720.
- [96] Chakraborty, Sagnik, Shamik Chowdhury, and Papita Das Saha. "Adsorption of crystal violet from aqueous solution onto NaOH-modified Rice Husk." *Carbohydrate Polymers* 86.4 (2011): 1533-1541.
- [97] Patil, C., G. M. Ratnamala, and S. T. Channamallayya. "Adsorption studies for removal of acid yellow 17 using activated Rice Husk." *Int Res J Eng Technol* 2.5 (2015): 769.
- [98] Guo, Yupeng, et al. "Adsorption of malachite green and iodine on Rice Husk-based porous carbon." *Materials chemistry and physics* 82.1 (2003): 107-115.
- [99] McKay, G., J. F. Porter, and G. R. Prasad. "The removal of dye colours from aqueous solutions by adsorption on low-cost materials." *Water, Air, and Soil Pollution* 114.3 (1999): 423-438.
- [100]Safa, Yusra, and Haq Nawaz Bhatti. "Kinetic and thermodynamic modeling for the removal of Direct Red-31 and Direct Orange-26 dyes from aqueous solutions by Rice Husk." *Desalination* 272.1-3 (2011): 313-322.
- [101]Ahmaruzzaman, M., and D. K. Sharma. "Adsorption of phenols from wastewater." *Journal of Colloid and Interface Science* 287.1 (2005): 14-24.
- [102]Imyim, Apichat, and Eakachai Prapalimrungsi. "Humic acids removal from water by aminopropyl functionalized Rice Husk ash." *Journal of Hazardous Materials* 184.1-3 (2010): 775-781.
- [103]Lataye, D. H., I. M. Mishra, and I. D. Mall. "Pyridine sorption from aqueous solution by Rice Husk ash (RHA) and granular activated carbon (GAC): parametric, kinetic, equilibrium and thermodynamic aspects." *Journal of Hazardous Materials* 154.1-3 (2008): 858-870.
- [104]Lataye, D. H.; Mishra, I. M.; Mall, I. D. Adsorption of α -picoline onto Rice Husk ash and granular activated carbon from aqueous solution: Equilibrium and thermodynamic study. *Chem. Eng. J.* 2009, 147, 139-149.
- [105]Kumagai, Seiji, et al. "Removal of dibenzothiophenes in kerosene by adsorption on Rice Husk activated carbon." *Fuel* 88.10 (2009): 1975-1982.
- [106]Yakout, S. M., and A. A. M. Daifullah. "Removal of selected polycyclic aromatic hydrocarbons from aqueous solution onto various adsorbent materials." *Desalination and Water Treatment* 51.34-36 (2013): 6711-6718.
- [107]Deokar, Sunil K., and Sachin A. Mandavgane. "Estimation of packed-bed parameters and prediction of breakthrough curves for adsorptive removal of 2, 4-dichlorophenoxyacetic acid using Rice Husk ash." *Journal of environmental chemical engineering* 3.3 (2015): 1827-1836.
- [108]Thakur, Chandrakant, et al. "Modelling of binary isotherm behaviour for the adsorption of catechol with phenol and resorcinol onto Rice Husk ash." *Indian chemical engineer* 59.4 (2017): 312-334.
- [109]Zhou, Yin, et al. "Land use and climate change effects on soil organic carbon in North and Northeast China." *Science of the Total Environment* 647 (2019): 1230-1238.
- [110]Pathak, Uttarini, et al. "Treatment of wastewater from a dairy industry using Rice Husk as adsorbent: treatment efficiency, isotherm, thermodynamics, and kinetics modelling." *Journal of Thermodynamics* 2016 (2016).
- [111]Zadeh, Reza Jazini, Mohammad Hossein Sayadi, and Mohammad Reza Rezaei. "Synthesis of Thiol modified magMCM-41 nanoparticles with Rice Husk ash as a robust, high effective, and recycling magnetic sorbent for the removal of herbicides." *Journal of Environmental Chemical Engineering* 9.1 (2021): 104804.
- [112]MOKASHI, SS. "A Comparative Study Of Defluoridation Of Water Using Bioadsorbents-Tea Waste And Rice Husk." (2020).
- [113]Mokashi, Mrs Sakshi S. "Defluoridation of Water by Rice Husk-A Bioadsorbent."
- [114]Rosa, Simone ML, et al. "Chlorine-free extraction of cellulose from Rice Husk and whisker isolation." *Carbohydrate Polymers* 87.2 (2012): 1131-1138.
- [115]Vickers, Neil J. "Animal communication: when i'm calling you, will you answer too?." *Current biology* 27.14 (2017): R713-R715.
- [116]Badar, Rabia, and Shamim A. Qureshi. "Composted Rice Husk improves the growth and biochemical parameters of sunflower plants." *Journal of Botany* 2014 (2014).
- [117]Suhag, Meenakshi. "Potential of biofertilizers to replace chemical fertilizers." *Int. Adv. Res. J. Sci. Eng. Technol* 3.5 (2016): 163-167.
- [118]Hanapi, Siti Zulaiha, et al. "Biofertilizer: Ingredients for Sustainable Agriculture." (2012).
- [119]Youssef, M. M. A., and M. F. M. Eissa. "Biofertilizers and their role in management of plant parasitic nematodes. A review." *Journal of Biotechnology and Pharmaceutical Research* 5.1 (2014): 1-6.
- [120]Ayala, Sankaram, and EVS Prakasa Rao. "Perspectives of soil fertility management with a focus on fertilizer use for crop productivity." *Current Science* 82.7 (2002): 797-807.
- [121]Sarin, Pornrapee, and Nuntavun Riddech. "Effects of Agricultural Residues as Carriers for Bio-fertilizer Production to Promote Tomato Growth in Saline Soil." *CHIANG MAI JOURNAL OF SCIENCE* 45.4 (2018): 1699-1712.
- [122]Ogbo, F. C., and M. O. Odo. "Potential of Rice Husk and cassava peel as carriers for bio-fertilizer production." *Nigerian Journal of Biotechnology* 23 (2011).
- [123]Anda, Markus, et al. "Changes in properties of composting Rice Husk and their effects on soil and cocoa growth." *Communications in soil science and plant analysis* 39.15-16 (2008): 2221-2249.
- [124]Jackson, A. M., J. M. Whipps, and J. M. Lynch. "Production, delivery systems, and survival in soil of four fungi with disease biocontrol potential." *Enzyme and microbial technology* 13.8 (1991): 636-642.
- [125]Bhattacharjee, Ritika, and Utpal Dey. "Biofertilizer, a way towards organic agriculture: A review." *African Journal of Microbiology Research* 8.24 (2014): 2332-2343.
- [126]Glick, Bernard R., et al. *Biochemical and genetic mechanisms used by plant growth promoting bacteria*. World Scientific, 1999.
- [127]Raja, P., et al. "Impact of bio inoculants consortium on rice root exudates, biological nitrogen fixation and plant growth." *J Biol Sci* 6.5 (2006): 815-823.
- [128]Verstraeten, Natalie, et al. "Living on a surface: swarming and biofilm formation." *Trends in microbiology* 16.10 (2008): 496-506.
- [129]Shahab, Sadaf, Nuzhat Ahmed, and Nasreen S. Khan. "Indole acetic acid production and enhanced plant growth promotion by indigenous PSBs." *African Journal of Agricultural Research* 4.11 (2009): 1312-1316.
- [130]Bashan, Y., and L. E. De-Bashan. "Plant growth-promoting." *Encyclopedia of soils in the environment* 1 (2005): 103-115.
- [131]Harun, Nur Saidahtul Nadiah, Noraini Md Jaafar, and Siti Zaharah Sakimin. "The effects of Rice Husk biochar rate on arbuscular mycorrhizal fungi and growth of soursop (*Annona muricata* L.) seedlings." *Sustainability* 13.4 (2021): 1817.
- [132]Maftuah, E., M. Saleh, and E. Pratiwi. "The potentials of biochar from agricultural waste as a carrier material of biofertilizer for swamplands." *IOP Conference Series: Materials Science and Engineering*. Vol. 980. No. 1. IOP Publishing, 2020.

- [133]Gauchan, Dhurva Prasad, et al. "Exploration of indigenous Trichoderma species for their use as biofertilizers, optimization of growth conditions and cultivation on cheap substrates." *Novel Research in Microbiology Journal* 4.4 (2020): 921-938.
- [134]Essoka, A. N., et al. "Characterization and rate of Rice Husk application for crop production." *ISOR Journal of Agriculture and Veterinary Sciences* 7.5 (2014): 44-47.
- [135]Hadi, Abdul, and Hasrul Satria Nur. "The Use of Biofertilizers Increased Plant Growth with No Trade-Off Effect on GreenHouse Gas Emission." *Journal of Wetlands Environmental Management* 5.1 (2017): 18-23.
- [136]Husni, M. H. A., and A. W. Samsuri. "Characterization of local mill Rice Husk charcoal and its effect on compost properties." *Malaysian Journal of Soil Science* 16 (2012): 89-102.
- [137]Zamoum, Miyada, et al. "Development of formulations based on Streptomyces rochei strain PTL2 spores for biocontrol of Rhizoctonia solani damping-off of tomato seedlings." *Biocontrol Science and Technology* 27.6 (2017): 723-738.
- [138]Jindal, Himanshu, Prabhjot Singh, and Hemant Bansal. "Evaluation of Thermal Conductivity of Insulations Prepared from Mixture of Rice Husk and Plaster of Paris." (2015).
- [139]IRENA: Heating & cooling retrieved from <https://www.irena.org/heatingcooling>
- [140]Alhabeeb, Baqer A., and Hayder N. Mohammed. "Investigating New Thermal Insulators Based on Cheap Natural Organic and Waste Materials: Part 1." *IOP Conference Series: Materials Science and Engineering*. Vol. 671. No. 1. IOP Publishing, 2020.
- [141]Ali, Majed H., and Layla M. Abass. "Ability of Agricultural Wastes Employ in Manufacturing of Thermal Insulator." *Euphrates Journal of Agriculture Science* 3.(2011) (9 العراق/ايران). عدد خاص بالمؤتمر الدولي الاول (العراق/ايران 9).
- [142]Justin, E. "Investigation on thermal properties of composite of Rice Husk, corncob and baggasse for building thermal insulation." *Volume 3 Issue 12–December 2014* (2014): 34.
- [143]GeerMax: The advantages and disadvantages of polystyrene foam insulation board retrieved from <http://www.styrofoamdensifier.org/the-advantages-and-disadvantages-of-polystyrene-foam-insulation-board/>
- [144]Liang, Han-Hsi, and Ming-Chin Ho. "Toxicity characteristics of commercially manufactured insulation materials for building applications in Taiwan." *Construction and Building Materials* 21.6 (2007): 1254-1261.
- [145]TS, Karthik, Kiran Ramaswamy, and Kavin RR. "Investigation on Dielectric Properties of Press Board Coated with Epoxy Resin, Quartz, and Rice Husk Ash." *Advances in Materials Science and Engineering* 2021 (2021)
- [146]Satta Panyakaew, Steve Fotios. "321: Agricultural Waste Materials as Thermal Insulation for Dwellings in Thailand: Preliminary Results." (2008).
- [147]Environmental, U. S. "PROTECTION AGENCY (2003)." *Hunter River Salinity Trading Scheme: Working together to protect river quality and sustain economic development*, Sydney: NSW EPA (2007).
- [148]Occupational Safety and Health Administration. "Synthetic mineral fibers: Health hazards." *United State Department of Labor* 76 (2003).
- [149]The U.S. Occupational Safety and Health Administration (OSHA), 1999. *the Health and Safety Partnership Program, the North American Insulation Manufacturers Association.*
- [150]Manohar, Krishpersad. "Renewable building thermal insulation—oil palm fibre." *International Journal of Engineering and Technology* 2.3 (2012): 475-479.
- [151]Zhou X, Zheng P.Z. Li. H. Lu. C. (2010) *An environmentally friendly insulation material from cotton stalk fibers energy and building* 42 1070-1074.
- [152]Guna, Vijaykumar, et al. "Valorization of sugarcane bagasse by developing completely biodegradable composites for industrial applications." *Industrial Crops and Products* 131 (2019): 25-31.
- [153]Eschenhagen, Arne, et al. "Investigation of miscanthus and sunflower stalk fiber-reinforced composites for insulation applications." *Advances in Civil Engineering* 2019 (2019).
- [154]Lacoste, Clément, et al. "Sodium alginate adhesives as binders in wood fibers/textile waste fibers biocomposites for building insulation." *Carbohydrate polymers* 184 (2018): 1-8.
- [155]Buratti, C., et al. "Rice Husk panels for building applications: Thermal, acoustic and environmental characterization and comparison with other innovative recycled waste materials." *Construction and Building Materials* 171 (2018): 338-349.
- [156]Binici, Hanifi, et al. "An environment-friendly thermal insulation material from sunflower stalk, textile waste and stubble fibers." *2013 International Conference on Renewable Energy Research and Applications (ICRERA)*. IEEE, 2013.
- [157]Palumbo, Mariana, et al. "Improvement of fire reaction and mould growth resistance of a new bio-based thermal insulation material." *Construction and Building Materials* 139 (2017): 531-539.
- [158]Wei, Kangcheng, et al. "Development and performance evaluation of a new thermal insulation material from rice straw using high frequency hot-pressing." *Energy and Buildings* 87 (2015): 116-122.
- [159]Wei, Liqing, Shaobo Liang, and Armando G. McDonald. "Thermophysical properties and biodegradation behavior of green composites made from polyhydroxybutyrate and potato peel waste fermentation residue." *Industrial Crops and Products* 69 (2015): 91-103.
- [160]Chabannes, Morgan, et al. "Use of raw Rice Husk as natural aggregate in a lightweight insulating concrete: An innovative application." *Construction and Building Materials* 70 (2014): 428-438.
- [161]Palumbo, Mariana, J. Formosa, and A. M. Lacasta. "Thermal degradation and fire behaviour of thermal insulation materials based on food crop by-products." *Construction and Building Materials* 79 (2015): 34-39.
- [162]Sekifujii, Ryoko, Chieu Le Van, and Masafumi Tateda. "Case study of fire flame resistance improvement of a plywood board coated with paint containing added Rice Husk amorphous silica." *Journal of Scientific Research and Reports* (2017): 1-9.
- [163]Guedert, Luis Otavio. "Estudo da viabilidade tecnica e economica do aproveitamento da cinza de casca de arroz com material pozolanico." (1989).
- [164]Bartha, P. "BIOGENOUS SILICIC ACID- A GROWING RAW MATERIAL." *Keramische Zeitschrift* 47.10 (1995): 780-785.
- [165]Gonçalves, M. R. F., and C. P. Bergmann. "Thermal insulators made with Rice Husk ashes: Production and correlation between properties and microstructure." *Construction and Building Materials* 21.12 (2007): 2059-2065.
- [166]Gonçalves, M. R. F., and C. P. Bergmann. "Thermal insulators made with Rice Husk ashes: Production and correlation between properties and microstructure." *Construction and Building Materials* 21.12 (2007): 2059-2065.

- [167] Chakrabarti, M., A. N. Virkar, and H. S. Maiti. "Formation of forsterite using Rice Husk ash for high frequency insulation." *Transactions of the Indian Ceramic Society* 44.1 (1985): 1-9.
- [168] Bakatovich, Aliaksandr, Nadezhda Davydenko, and Florindo Gaspar. "Thermal insulating plates produced on the basis of vegetable agricultural waste." *Energy and Buildings* 180 (2018): 72-82.
- [169] Muthuraj, Rajendran, et al. "Sustainable thermal insulation biocomposites from Rice Husk, wheat husk, wood fibers and textile waste fibers: Elaboration and performances evaluation." *Industrial Crops and Products* 135 (2019): 238-245.
- [170] Hossain, SK Saddam, et al. "Preparation of forsterite refractory using highly abundant amorphous Rice Husk silica for thermal insulation." *Journal of Asian Ceramic Societies* 5.2 (2017): 82-87.
- [171] Musa, Mohamad Nor, and Mohamed Fikhri Abdul Aziz. "Thermal conductivity for mixture of Rice Husk fiber and gypsum." *Applied Mechanics and Materials*. Vol. 819. Trans Tech Publications Ltd, 2016.
- [172] da Rosa, Leandro Cantorski, et al. "Use of Rice Husk and sunflower stalk as a substitute for glass wool in thermal insulation of solar collector." *Journal of Cleaner Production* 104 (2015): 90-97.
- [173] Junaidi, M. U. M., et al. "Near superhydrophobic coating synthesized from Rice Husk ash: Anti-fouling evaluation." *Progress in Organic Coatings* 99 (2016): 140-146.
- [174] Das, Sonalee, et al. "A review on superhydrophobic polymer nanocoatings: recent development and applications." *Industrial & Engineering Chemistry Research* 57.8 (2018): 2727-2745.
- [175] Junaidi, M. U. M., et al. "Superhydrophobic coating of silica with photoluminescence properties synthesized from Rice Husk ash." *Progress in Organic Coatings* 111 (2017): 29-37.
- [176] Junaidi, M. U. M., et al. "Near superhydrophobic coating synthesized from Rice Husk ash: Anti-fouling evaluation." *Progress in Organic Coatings* 99 (2016): 140-146.
- [177] Doran, David, and Bob Cather, eds. *Construction materials reference book*. Routledge, 2013.
- [178] Sahoo, Bichitra Nanda, and Balasubramanian Kandasubramanian. "Recent progress in fabrication and characterisation of hierarchical biomimetic superhydrophobic structures." *Rsc Advances* 4.42 (2014): 22053-22093.
- [179] Ahmad, N. A., et al. "Membranes with great hydrophobicity: a review on preparation and characterization." *Separation & Purification Reviews* 44.2 (2015): 109-134.
- [180] Rykaczewski, Konrad, et al. "Dynamics of nanoparticle self-assembly into superhydrophobic liquid marbles during water condensation." *Acs Nano* 5.12 (2011): 9746-9754.
- [181] Ahmad, N. A., C. P. Leo, and A. L. Ahmad. "Synthesis of superhydrophobic alumina membrane: Effects of sol-gel coating, steam impingement and water treatment." *Applied surface science* 284 (2013): 556-564.
- [182] Xue, Chao-Hua, et al. "Washable and wear-resistant superhydrophobic surfaces with self-cleaning property by chemical etching of fibers and hydrophobization." *ACS applied materials & interfaces* 6.13 (2014): 10153-10161.
- [183] Liu, Zhanjian, et al. "Superhydrophobic poly (vinylidene fluoride) membranes with controllable structure and tunable wettability prepared by one-step electrospinning." *Polymer* 82 (2016): 105-113.
- [184] Ma, Minglin, et al. "Superhydrophobic fabrics produced by electrospinning and chemical vapor deposition." *Macromolecules* 38.23 (2005): 9742-9748.
- [185] Si, Yifan, and Zhiguang Guo. "Superhydrophobic nanocoatings: from materials to fabrications and to applications." *Nanoscale* 7.14 (2015): 5922-5946.
- [186] Wenzel, Robert N. "Resistance of solid surfaces to wetting by water." *Industrial & Engineering Chemistry* 28.8 (1936): 988-994.
- [187] Kumar, Divya, Lin Li, and Zhong Chen. "Mechanically robust polyvinylidene fluoride (PVDF) based superhydrophobic coatings for self-cleaning applications." *Progress in Organic Coatings* 101 (2016): 385-390.
- [188] Caldon, Eugene B., et al. "Preparation of spray-coated surfaces from green-formulated superhydrophobic coatings." *SN Applied Sciences* 1.12 (2019): 1-9.
- [189] Contraception, H. O. R. M. O. N. A. L., and H. Therapy. "IARC monographs on the evaluation of carcinogenic risks to humans." Lyon: International Agency for Research on Cancer (1999).
- [190] Pode, Ramchandra. "Potential applications of Rice Husk ash waste from Rice Husk biomass power plant." *Renewable and Sustainable Energy Reviews* 53 (2016): 1468-1485.
- [191] Das, Sonalee, et al. "A review on superhydrophobic polymer nanocoatings: recent development and applications." *Industrial & Engineering Chemistry Research* 57.8 (2018): 2727-2745.
- [192] Husni, H., et al. "Superhydrophobic Rice Husk ash coating on concrete." *Construction and Building Materials* 144 (2017): 385-391.
- [193] Anitha, C., and Sundar Mayavan. "Salvinia inspired fluoroine free superhydrophobic coatings." *Applied Surface Science* 449 (2018): 250-260.
- [194] Anitha, C., S. Syed Azim, and Sundar Mayavan. "Fluorine free superhydrophobic surface textured silica particles and its dynamics-Transition from impalement to impingement." *Journal of Alloys and Compounds* 711 (2017): 197-204.
- [195] Husni, H., et al. "Superhydrophobic Rice Husk ash coating on concrete." *Construction and Building Materials* 144 (2017): 385-391.
- [196] Shishodia, Abhilash, et al. "Multidimensional durability of superhydrophobic self-cleaning surface derived from rice-husk ash." *Progress in Organic Coatings* 136 (2019): 105221.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)