



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 5 Issue: XI Month of publication: November 2017

DOI:

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Improving Strength in Brick Column by Providing Electro Welded Wire Mesh

Tanveer Ahmad Dar¹, Uzair Ahmad Bhat²

^{1,2}Department of civil engineering, gulzar group of institutes khanna, Ludhiana

Abstract: This research paper has been selected to explore the procedure of making the brick masonry columns more strong and durable in resisting the compressive forces by using the wire mesh and hence reduces the cross sectional area of column, which increases our floor area. The size of wire mesh is 2mm diameter of wire and 15mm X 15mm spacing. Three samples of sizes 9 inch X 9 inch have been used. Out of which the sample no. 1 is simple and In sample no. 2 & 3 wire mesh have been placed in the odd and even mortar joints (coarse no.1, coarse no.3, coarse no. 5 & coarse no. 2, coarse no.4). The ratio of Cement & Mortar is kept same for all the samples i.e. 1:3 (one part of cement and three parts of sand). The tests shows that the sample no.2 gave the strength 1.9 times the strength of sample no. 1 and sample no.3 gave the strength 1.8 times the strength of sample no.1. Thus the columns become stronger and columns also show ductile behavior during failure.

I. INTRODUCTION

A. General

Brick masonry columns are constructed in a variety of structures – homes, private and public buildings. Their main function is to resist the compressive forces. But due to the least compressive strength many brick masonry units especially columns become unsafe and require economical, safe and easy techniques to meet the required needs.

In this study, brick masonry columns were strengthened by using wire mesh of same size and it was kept in mind that the conditions suit to the actual site conditions and not the laboratory conditions, so that's why all the columns were casted in open air fully expose to the atmospheric conditions and the method of casting resemble to the general practice. In this study effort has been made to increase the compressive strength without increase in the cross – sectional area and the dead load of columns using commonly available wire mesh.

B. Scope and limitations

The study deals with the application of wire mesh in the horizontal mortar joints. The following parameters are kept constant in the study

- 1) Ratio of mortar for brick masonry work equal to 1:3 (1 part cement, 3 parts sand).
- 2) Size of brick masonry columns equal to 9 in. x 9 in. x 20.5 in. (length x width x height).
- 3) Three samples with each sample having two sub samples that means total of 6 columns were casted of same size.
- 4) Two of the samples are reinforced with a wire mesh in between the brick courses (one in even courses and other in odd courses).
- 5) It should be noted that the grade of cement is OPC 53.

II. METHODOLOGY

A. General

All the masonry columns were prepared under ordinary conditions having mix proportion of 1:3. There were 6 columns of same size. All the specimens were moist cured air dried in open air for 28 days before testing. The testing was carried out after 28 days of casting of specimens.


B. Procedures For Casting Different Samples

All the samples were casted with almost same procedure but the difference lies in the arrangement of providing the reinforcing materials. Before casting the bricks are soaked into the water for about 24hrs and then they are air dried. The next step is the preparation of the mortar in which the sand and cement are first dry mixed and then water is added to this dry mix. Water is added in such a way that the mortar becomes workable for a mason as it has to resemble with the general practice. The bricks are laid in such


a way that in the first course stretcher face is laid along the length and in the second course header face of the bricks are laid along the length. This arrangement is provided in order to break the continuity of the mortar joints. The procedures for casting of different samples are given below:




- 1) *Sample no. 1:* As discussed earlier that the sample no.1 is simple which means that it is not reinforced with any material. In this the bricks are laid on a prepared platform which is mainly of wood and the mortar thickness is kept $\frac{1}{2}$ inch. As shown in figure below



- 2) *Sample no. 2:* In sample no. 5 wire mesh is embedded in the odd mortar joints in the form of squares of dimensions same as the column cross – section provided with a clear cover of about ¼ inch on all sides. As shown in figure below:



- 3) *Sample N3) :* In this sample wire mesh is embedded in the even mortar joints in the form of squares of dimensions same as the column cross - -sction provided with a clear cover of ¼ inch on all sides



C. *Testing*

- 1) *Test of sample no. 1:* In case of plane brick columns, all the two samples show brittle failure. Major cracks were vertical, however, few horizontal cracks were also observed. The vertical cracks passed through the joints and bricks, while horizontal cracks were through joints only. he cracks widening and propagation was quite fast after their first appearance. Near failure, the specimen demonstrated outwardbulging on all four faces. As shown in figure below:



Failure pattern of sample no. 1

- 2) *Test of sample no. 2:* In this case wire mesh is placed in the odd horizontal joints i.e. 1, 3 & 5. The column develops the very few minute vertical cracks on application of axial load. The vertical cracks fail to pass through the reinforced joints and no horizontal cracks were developed. The crack growth was quite stable and widening rate was much slower than the other samples. This slow rate of crack growth can be attributed to wire mesh presence inside the joints which helped in arresting the cracks during their propagation process.



Failure pattern of sample no. 2


- 3) *Test of sample no. 3:* In this case wire mesh is placed in the even horizontal joints i.e. 2, 4. The column develops the major cracks vertically as well as horizontally while applying the axial loads. The vertical cracks fail to pass through the reinforced joints but the face of the column bulges out at the centre above the reinforced joint due to the restrictions developed by mesh. Near failure small chunks of bricks and mortar fell of the specimen, but no significant spilling was observed.



Failure pattern of sample no.3

| SAMPLE NO. | SAMPLE DESCRIPTION | MAX. FAILURE LOADS OF SUB - SAMPLES | AVERAGE | PERCENTAGE INCREASE IN THE STRENGTH WITH REFERENCE TO SAMPLE NO.1 |
|------------|--|-------------------------------------|---------|---|
| 1 | SIMPLE | 86 KN | 86.5 KN | - |
| | | 87KN | | |
| 2 | WIRE MESH PLACED IN ODD HORIZONTAL JOINTS | 186 KN | 170 KN | 96.5% |
| | | 154KN | | |
| 3 | WIRE MESH PLACED IN EVEN HORIZONTAL JOINTS | 132 KN | 159 KN | 83.8% |
| | | 186KN | | |

Test results of various samples



Comparison between the strengths of various samples

III. CONCLUSIONS

Firstly, the application of wire mesh enhances the compressive strength of brick masonry columns. As seen that the sample having wire mesh placed in the odd horizontal joints showed an increase in failure load upto 96.5% as compared to the simple brick masonry column. Wire mesh and mortar layer acts as a slab between the respective joints prevents from the deep vertical cracks. Secondly, the cracking resistance and stable crack growth mechanism of simple masonry columns improved due to the application of wire mesh. Lastly, the failure of brick masonry columns is very sudden and cracks widen rapidly after their formation leading to a brittle failure of the structure.

IV. ACKNOWLEDGEMENT

This research is supported by Mrs. Aina Arora. I am very thankful to our college Govt. Polytechnic College Pulwama, campus IUST Awantipora and Gulag Group of Institutes for providing us such a platform to exhibit our talent. They provided us all facilities and experts which supported us in every field. This research is done under the supervision of Er. Sajad Ahmad Khan and H.O.D S. JogaSingh. I proudly thank them. Also, I am very thankful to my parents and my friends particularly Syed Zeeshan, Altaf Ahmed, ZamirIrfan, Azhar Gull, Sohail Aziz, Syed Muneer and Muzammil Agawho gave me lot of support in making this task successful.

REFERENCES

- [1] Vergilis, Cheryl. "Everything You Need to Know About Welded Wire Mesh Fence Panels". Retrieved 2017-02-21.
- [2] "Column - Definition and More from the Free Merriam-Webster Dictionary". Merriam-webster.com. 2012-08-31. Retrieved 2013-07-04.
- [3] Hewson Clarke and John Dougall, The Cabinet of Arts, T. Kinnersley, London (1817).
- [4] J. Ward-Perkins, "The shrine of St. Peter's and its twelve spiral columns" Journal of Roman Studies (1952).
- [5] Sanseverino, Hilary Costa (1983). "Archaeological Remains on the Southern Somali Coast". Azania: Archaeological Research in Africa Retrieved 11 November 2014.
- [6] MihaTomazevic, 2000 "Earthquake – Resistant Design of Masonry Buildings" series on innovation in structures and construction – volume – 1, Imperial College London.
- [7] P. Sheppard and S. Tercelj p, 1980 "The Effect of Repair and Strengthening Methods
- [8] Universidad nacional de ingenieria (UNI), "March 2004, Masonry Construction Guide Lima – Peru".
- [9] Master thesis of Engr. Khan Shahzada "Building Research Institute Tsukuba Japan 2007.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)