



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 8

Issue: IV

Month of publication: April 2020

DOI:

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Study the Adsorption Potential of Bioadsorbent Derived From the Seeds of *Strychnos Potatorum* with the Reference of Methylene Blue Dye

Usma Gangwar¹, Dr Anita Choubey²

¹Master in chemistry from RDVV University of Jabalpur;

²Professor(PhD scholar in chemistry), MLB College Bhopal.

Abstract: *The essential objective of the present examination was to assess the plausibility of insignificant exertion adsorbent got from the seeds of *Strychnos potatorum* for the ejection of MB from fluid arrangement in group framework. The effects of different parameters including different pH, biosorbent portion, starting color fixation and contact time were mulled over. *Strychnos potatorum* Linn. is an imperiled woods tree. It is has a spot with Loganiaceae family and is generally called nirmali and clearing nut tree.*

*The results revealed that the adsorption furthest reaches of actuated carbon of *Strychnos potatorum* was high over methylene blue.*

The adsorptive assessment was applied in group analyze as a part of contact time, adsorbent bit, arrangement pH and starting obsession, where adsorption of MB is significantly affected by the adsorbent segment, time, introductory MB fixation, pH.

The results exhibited more significant level of MB ejection at lower starting shading fixation and the balance between MB in the arrangement and the half adsorbent surface was in every practical sense drenched in 20 min.

Index Terms: *Strychnos potatorum, methylene blue, Bioadsorption, kinetic isotherm, Batch experiment, activated carbon.*

I. INTRODUCTION

Strychnos potatorum Linn.F. is a significant jeopardized woods tree. It is has a spot with Loganiaceae family and is generally called nirmali and clearing nut tree [1]. it has been used comprehensively as a legends tranquilize and in ayurvedic practice, conspicuously the common item as an antidiabetic, antidystentric, emetic, while the squash is important as an expectorant [2]. It is a medium-sized, glabrous tree of height 12-13 m. Stem is fluted and verified with dull, thick, square to rectangular scales and Seeds are hard globose alive and well [3].

A couple of examiners have been represented the water filtration capacity of trademark *Strychnos potatorum* seed [4, 5, 6]. Keeping an eye on a couple of issues of compound purifiers gets out for a goliath proportion of research to be coordinated to recognize incredible new systems for cleaning water at lower cost and with less imperativeness, while at the same time restricting the use of engineered blends influence on nature [7].

There are various strategies for dirtying water, most noteworthy being the arrival of current waste water through spillage from into water bodies. The sewage discharge from homes isn't treated before being discharged to condition which is moreover an essential driver of sullyng. wastewater is one of the significant common issues rising in various thickly populated and present day locales of the world. Move of business and industry vehicle wash wastewater can speak to a gigantic hazard to the prosperity of our channels [8].

Colors have been excessively released into nature on account of speedy industrialization and have made a huge overall concern [9]. The amount of material associations in Korea related to shading is 360,616 out of 2015, equivalent to 3.6% of full scale wastewater discharging workplaces.

In any case, shading wastewater outpouring speaks to 22.2% of outright wastewater release [10].

The standard objective of the present assessment was to overview the likelihood of insignificant exertion adsorbent got from the seeds of *Strychnos potatorum* for the ejection of MB from watery arrangement in bunch system. The effects of different parameters including arrangement pH, biosorbent estimation, starting color focus and contact time were considered. Additionally, the isotherm and engine parameters were researched to depict the exploratory data.

II. MATERIALS AND METHODS

A. Selection of Biomass for Activated Carbon Preparation

In the present examination, seeds of *Strychnos Potatorum* were utilized as antecedents for the planning of actuated carbon. *Strychnos Potatorum*, seeds were gathered from backwoods territory of Kerwa dam, Bhopal, Madhya Pradesh, India, (Figure 1). It is a minimal effort and richly accessible plant found in the timberland zone.



Figure 1 *Strychnos Potatorum* seeds

B. Chemical Activation and Planning of Activated Carbon

The dried materials of seeds were utilized for the planning of actuated carbons utilizing concoction enactment techniques. The concoction impregnation of the initiating operator into the *Strychnos potatorum*. The antecedents were then immersed in conc. orthophosphoric corrosive for span of 24 hours. From that point forward, material was carbonized at 400°C by putting it in the suppress heater. The dried materials were powdered and initiated in a mute heater for span of an hour kept at 800°C. After actuation, the carbon gathered was washed satisfactorily with a lot of water and dried 80 at that point sieved to required molecule size [11] (Figure 2).



Figure 2 Activated carbon of *Strychnos potatorum* seeds

MB dynamic and isotherm adsorption tests were finished to survey the adsorption execution. The harmony adsorption investigate was done by including a fixed proportion of initiated carbon into 50 ml unmistakable early on groupings of MB. The dynamic adsorption considers were performed by including 0.1 g started carbon into 50 ml unmistakable starting groupings of MB. The liquid models were taken at pre-set time intervals and their centers were settled. Center affirmation of the impressive number of tests was filtered before they were evaluated by UV-6100A spectrophotometer at the most extraordinary ingestion wavelength of 660 nm. The proportion of MB adsorption at amicability was controlled by

$$q_e = (C_o - C_e)V/W$$

where C_o and C_e (mg/L) are the underlying and balance groupings of MB, individually, V (L) is the volume of the arrangement, and W (g) is the mass of adsorbents utilized. The take-up of MB at time t , q_t (mg/g) was determined by

$$q_t = (C_o - C_t)V/W$$

where C_t is the convergence of MB whenever.

III. RESULTS

Adsorption tests were performed in batch mode at room temperature. So as to break down the idea of activated carbon and MB collaboration, at first the impact of pH on % adsorption was completed and afterward further examinations on the effect of contact time, starting focus, and adsorbent portion was led on upgraded pH. Just a single parameter was modified at a time remaining others were kept consistent.

A. Effect of pH

The impact of pH on the balance adsorption of MB color was researched by utilizing an underlying grouping of MB of 50 mg/L and 0.1 g/50 mL of initiated carbon. Figure-3 shows the variety in the adsorption of MB from watery arrangement. This outcome might be because of the hydrophobic idea of created activated carbon, which causes the adsorption of H⁺ particles on the outside of carbon [12]. As the carbon surface is adversely charged at higher pH, a normally lively electrostatic fascination turns out in the middle of the contrarily charged carbon surface and color particles, bringing about the maximal adsorption of MB [13].




Figure -3 Effect of pH on Adsorption of MB

B. Impact of Adsorbent Dose

The investigation of the adsorption of MB on enacted carbon was finished by changing the measure of adsorbent (0.1-0.5 g/50 mL) in the test arrangement next to that keeping up the underlying MB fixation (100 mg/L) and pH (7.0) consistent at contact time for 20 min. Figure-4 shows that the adsorption of MB expanded from 42.7 % to 68.9 % as the adsorbent portion climbed from 0.1 g to 0.5 gm at the balance time of 20 min. Greatest MB disposal was accomplished in the time scope of 10 to 50 min, after which convergence of MB in the arrangement remains practically steady.




Figure -4. Effect of Adsorbent Dose on Adsorption of MB

C. Effect of Contact Time

The investigation runs estimating the impact of contact time (10 - hour long) on the group adsorption of MB at starting pH esteem 7, introductory MB centralization of 100 mg/L and with 0.1 g/50 mL adsorbent portion demonstrated that expansion in contact time from 10 to hour long upgraded the % adsorption of MB fundamentally. Figure 5 shows that more than 40 % of MB adsorption accomplished in the initial 20 min, later the level of adsorption of MB onto initiated carbon was moderate.




Figure -5 Effect of Contact Time on adsorption of MB

D. Effect of MB fixation

The examinations were performed with fixed adsorbent portion (0.1 g/50 mL) in the test arrangement at room temperature, pH 7 with differing starting centralization of MB (50, 100, 150, 200 and 250 mg/L) for contact time of 20 minutes. Figure-6 delineates that the adsorption level of actuated carbon lessens with the augmentation of beginning MB fixation in the arrangement. The adsorption limit with regards to enacted carbon was expanded from 29.2 to 54.6 mg/g as the MB fixation climbed from 50 to 250 mg/L. In the system of MB adsorption essentially, color particles have first to experience the limit impact, after that they need to diffuse over the limit layer film into the adsorbent surface and in any event they need to diffuse into the permeable structure of the adsorbent. This episode will take practically longer contact time.

Figure -6 Effect of MB Concentration on Adsorption

E. Isotherm Data Analysis

The Langmuir and Freundlich isotherm is plotted and appeared as Figure-7 and Figure 8 and the outcomes got from the Langmuir and Freundlich isotherm model for the disposal of MB onto enacted carbon are condensed in Table-1. The pertinence of the direct type of both the models to initiated carbon was demonstrated by the high relationship coefficients, R² greater than 0.93. This recommends the both the models give a decent model of the sorption framework. It will be noticed that the estimation of 1/n was somewhere in the range of 0 and 1 showing the adsorbent arranged are good for adsorption of the MB.

Table-1 Comparison of The Coefficients Isotherm Parameters for MB Adsorption

Isotherm Model	Coefficients Isotherm Parameters		
	Q _m (mg/g)	b (L/mg)	R ²
Langmuir	50	0.0195	0.988
Freundlich	1/n	K _f (mg/g)	R ²
	0.48	2.07	0.938




Figure-7 Linear plot of Langmuir isotherm for MB adsorption




Figure-8 Linear plot of Freundlich Isotherm for MB Adsorption

F. Dynamic Studies

The congruity among exploratory information and the model anticipated worth was delineated through the relationship coefficients (R2, values close or equivalent to 1) [14]. Similarly more prominent worth is the most extreme reasonable model for the energy of MB adsorption onto initiated carbon.




Figure-9 Pseudo First order Kinetic Plot for the Adsorption of MB




Figure-10 Pseudo Second order Kinetic Plot for the Adsorption of MB

The straight line plots of $\log (Q_e - Q_t)$ against time for the pseudo-first-demand reaction and t/Q_t against time for the pseudo-second-demand reaction of the adsorption of MB onto ordered carbon are showed up in Figure-9 and 10. The decided estimation of k_1 , k_2 , Q_e and their relating backslide coefficient regards (R^2) are presented in Table-2.

The association coefficients for the first and second solicitation engine model were 0.101 and 0.969, which drove us to expect that the pseudo second solicitation dynamic model passes on a predominant relationship for MB adsorption on established carbon. The estimation of beginning sorption (h), which shows that the level of early on adsorption is 1.91 mg (g/min).

Table-2 Pseudo First and Second order Kinetic Constant for Adsorption of MB

Q _e	First-order Kinetic Model			Second-order Kinetic Model			
	k ₁	Q _e Calculated	R ²	k ₂	Q _e Calculated	h	R ²
11	0.016	1.69	0.101	0.0144	11.5	1.91	0.969

[k₁ (min⁻¹), k₂ (mg min⁻¹), Q_e (mg g⁻¹), h, mg (g min⁻¹)]

IV. CONCLUSION

In the present examination, to think about the adsorption capability of initiated carbon arranged from the seeds of *Strychnos potatorum* plant utilized for evacuation of methylene blue. The outcomes uncovered that the adsorption limit of enacted carbon of *Strychnos potatorum* was high over methylene blue. The adsorptive assessment was applied in group investigates as a segment of contact time, adsorbent bit, game plan pH and starting center, where adsorption of MB is particularly influenced by the adsorbent segment, time, introductory MB focus, arrangement pH. The results demonstrated more elevated level of MB removal at lower beginning shading centers and the harmony between MB in the game plan and the half adsorbent surface was basically drenched in 20 min.

REFERENCES

- [1] JGangwar U, Chowbey A: Pharmacological And Phytochemical Importance Of *Strychnos potatorum* Linn. (F): A Review. Asian Journal of Pharmaceutical Education and Research, 2017; Vol 6, Issue 1: 52-59.
- [2] Biswas A, Chat S, Terjee, Chowdhury R, Sen S, Sarkar D, Chatterjee M And Das J. Antidiabetic Effect Of Seeds Of *Strychnos Potatorum* Linn. In A Streptozotocin-Induced Model Of Diabetes. Acta Poloniae Pharmaceutica Drug Research, 2012; Vol. 69 No. 5: pp. 939-943.
- [3] Alwe JR and Alwe RS. Pharmacognostic Study Of *Strychnos Potatorum* Linn -A Review]. International Ayurvedic Medical Journal {Online} 2016 { [Http://www.lamj.in/posts/images/upload/1222_1226.Pdf](http://www.lamj.in/posts/images/upload/1222_1226.pdf).
- [4] Deshmukh BS, Pimpalkar SN, Rakhunde RM and Joshi VA. Evaluation Performance of Natural *Strychnos potatorum* over the Synthetic Coagulant Alum, for the Treatment of Turbid Water. International Journal of Innovative Research in Science, Engineering and Technology, 2013; Vol. 2, Issue 11: 6183-6189.
- [5] Radin Mohamed RMS , Abdul Rahman N and Mohd Kassim AH. Moringa Oleifera and *Strychnos potatorum* Seeds as Natural Coagulant Compared with Synthetic Common Coagulants in Treating Car Wash Wastewater: Case Study 1. Asian Journal of Applied Sciences, 2014; Volume 02 – Issue 05: 693-700.
- [6] Vijayaraghavan G, Sivakumar T, Vimal Kumar A. Application of Plant Based Coagulants for Waste Water Treatment, International Journal of Advanced Engineering Research and Studies, 2011; 1(1):88-92
- [7] Packialakshmi N, Suganya C, Guru V. Studies On *Strychnos potatorum* Seed And Screening The Water Quality Assessment Of Drinking Water. International Journal of Research in

Pharmaceutical and Nano Sciences, 2014; 3(5): 380 - 396.

- [8] SenthilKumar P, Vaibhav KN, Rekhi S, Thyagarajan A. Removal of turbidity from washing machine discharge using Strychnos potatorum seeds: Parameter optimization and mechanism prediction. Resource-Efficient Technologies, 2016; Volume 2, Supplement 1: S171-S176.
- [9] Abdelkarim S, Mohammed H, Nouredine B. Sorption of Methylene Blue Dye from Aqueous Solution Using an Agricultural Waste. Trends Green Chem. 2017, 3:1.
- [10] Choi H, Yu SW. Biosorption of methylene blue from aqueous solution by agricultural bioadsorbent corncob. Environmental Engineering Research, 2019; 24(1): 99-106.
- [11] Rajamani R, Vinoth kumar, Sujith A and Karthick E: Activated Carbon Production from Waste Biomass. International Journal of Engineering & Technology, 2018; 7 (3.34):345-348.
- [12] Alzaydien AS: Adsorption of methylene blue from aqueous solution onto low cost natural Jordanian tripoli' American J. Environ. Sciences, 2009; 5 (3):197-208.
- [13] Bhattacharya KG and Sharma A: Kinetics and thermodynamics of methylene blue adsorption on neem (Azadirachta indica) leaf powder' Dyes and pigments, 2005; 65, 51-59.
- [14] Kannan N and Sundaram MM: Kinetics and mechanism of removal of methylene blue by adsorption on various carbons- A comparative study' Dyes and Pigments, 2001; 51: 25-40.

AUTHORS PROFILE

Author-
Photo

DR ANITA CHOUBEY is a professor at MLB College Bhopal. She is PhD scholar in chemistry & her area of interest lies in adsorption chemistry.



USMA GANGWAR has done Master in chemistry from RDVV University of Jabalpur. She has more than 8 years experience as a research scientist in a prestigious pharmaceutical company. She has also qualified MPSET & GATE in chemistry. Her area of interest lies in Nano chemistry.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)