



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 9 Issue: VI Month of publication: June 2021

DOI: <https://doi.org/10.22214/ijraset.2021.35218>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Shrinkage Elimination in Casting of GG30 Grade Cast Iron Impellor by using Pro-cast Software & Finite Elemental Analysis by Meshcast Software

Vaibhav Maniyar

Mechanical Department, Government Polytechnic, Jamnagar

Abstract: *There are 100+ submersible pump manufacturers in Rajkot Engineering Cluster. So, there are 100 plus foundry engaged in casting of cast iron impellor for submersible pump. They face shrinkage defect after casting and about 10 % rejection is because of shrinkage.[1] So in order to reduce this defect casting simulation software is very helpful. By using Pro-Cast simulation software mould of impellor is imported in Pro-Cast software and by applying sand mould condition, pouring temperature, pouring time etc. are put into the software, and finally result shows the areas of impellor where shrinkage chances are more.*

Keywords: *Pro-Cast, Cast Iron, Submersible pump*

I. INTRODUCTION

Casting is old and important production process in manufacturing sector. Where mould cavity form by using sand mould, and molten metal is poured into the mould and after solidification done, as cast product can be produced.[2]

II. LITERATURE REVIEW

Guidelines for effective implementation and the best practices for efficient use of casting simulation technology are presented here. These are based on a comprehensive review of about 200 industrial projects carried out by simulation consultants associated with IIT Bombay. The projects are of two types: (a) quality or yield improvement of existing castings, and (b) rapid development of new castings. The guidelines cover all major metals and processes, and deal with five stages of simulation projects: data gathering, methods design, numerical simulation, method optimization, and project closure. Major concerns: how to obtain accurate results, reduce total lead time, and ensure data security are addressed, and illustrated with industrial examples [3]. Casting defects are usually easy to characterize but to eradicate them can be a difficult task. Defects are caused by combined effect of different factors, whose identification is often difficult. Casting process involves complex interactions among various parameters and operations related to metal composition, methods process, melting, pouring, machining. Presence of these defects exposes foundries to contribute over 70% of total quality costs. Foundries try to reduce rejections by experimenting with process parameters (like alloy composition, mould coating and pouring temperature). When these measures are ineffective, then methods design (gating and feeding) is modified.[4]. Computer simulation technique and design of experiment used for casting defects analysis. In the first part using casting simulation technique analysis for shrinkage porosity defect is performed and new gating system designed. Number of iterations performed using simulation software to achieve optimum design. With new gating system reduction in shrinkage by (about 2.85 %) and yield improvement by (about 9.85 %) is observed. In the second part DOE used for casting defects analysis so sand related and pouring practices related parameters considered are moisture content, sand particle size, mould hardness and pouring temperature. Taguchi based L9 orthogonal array was used for the experimental purpose and analysis was carried out using Minitab software for analysis of variance (ANOVA).[5]. Casting defects can be defined as the departure from conformance to customer requirements, with respect to (i) geometry: ex. mismatch and swell, (ii) integrity: ex. porosity and inclusions, and (iii) property: ex. segregation and hard spots. The resulting loss of foundry productivity and customer confidence is a heavy price to pay. Jobbing foundries encounter a higher level of defective castings, averaging 8-15%. Even production foundries have overall 3-6% defective castings [6],[7] Metal casting is one of the direct methods of manufacturing the desired geometry of component. The method is also called as *near net shape process*. It is one of the primary processes for several years and one of important process even today in the 21st century. Early applications of casting are in making jewelry items and golden idols. Today, casting applications include automotive components, spacecraft components and many industrial & domestic components, apart from the art and jewelry items. [8],[9]. Solidification of metal is the process phase transformation of the liquid phase to solid phase with the liberationism of latent heat of fusion.

Metal solidification phenomenon is the great interest to casting engineers, metallurgist and software developers. It influences directly the quality of casting, production cycle time and utilization of materials (yield of casting). During this phase transformation process, it developed casting defects like shrinkage, hot tears, and porosity. To minimize these defects, the accuracy of proper design of casting and gating system is the basic necessity. We can predict those defects with casting design by means of numerical optimization (simulation) of casting solidification. In this paper, by using Auto cast –X simulation software we made modification in gating system and develop casting free from defect, in particular, shrinkage defect.

III.METHODOLOGY

The experimental work carried out at small scale unit engaged in casting of cast iron impellor.. When casting defect inspection was completed on casting major shrinkage defect was found. Due shrinkage defect, due to shrinkage defect cast iron impellor were rejected and 10 to 12 % rejection is observed during ultrasonic testing. Simulation is the process of imitating a real phenomenon using a set of mathematical equations implemented in a computer program.

In casting numerical simulation, the activity like, filling of molten metal into the mould and solidification process analysis is done with the help of algorithm or program based on vector element based, the simulation used to identify the hot spots and defects like shrinkage porosities, hot tears, cracks, etc. The casting solid 3D model has to be created using a solid modeling system e.g. solid works and imported into the simulation software, further analysis. B.ravi [11] has suggested casting simulation and optimization methodology.

IV. EXPERIMENTAL DATA FOR IMPELLER

The component for casting process is impellor for the centrifugal pump made of gray iron material. The required grade for the casting is as per GG30 grade by sand casting process. The pouring temperature, pouring time, runner weight and riser weight all the details cover under following table 1 as shown below.

Table 1: Specification of impellor

Sr. No.	Parameter	Value
1	Pouring temp	1440 ⁰ C
2	Composition of casting	C-2.50%, Si-2.61%, Mn-0.39%, Si-2.90%, P-0.033%
3	Part No.	R34
4	Material	C.I GG-20
5	Weight	5 Kg
6	Bath Metal	C-2.9 to 3.76,Si-1.56 to 1.75,Extra add Mn-250gms
7	Runner riser total weight	6 kg
8	Pouring Time	5.0 Sec
10	Density	7000 kg m ⁻³
11	Co. of Thermal exp.	1.1e-005 C ⁻¹
12	Specific Heat	447 J/kg C
13	Thermal Conductivity	52 W/m C
14	Resistivity	9.6 e-008 ohm m
15	Mould size	228.6 X 330.2 mm

V. MODELING AND FINITE ELEMENT ANALYSIS OF IMPELLER USING PROCAS

A. Modelling of Impeller is Performed using SOLID Works 2009

Figure1 shows Impeller 3D Model. In Impeller Casting Process, two impellers are cast in single mould. Therefore, we have to prepare assembly of two impellers with actual runner and riser. It is shown in fig. 1




Fig 1. 3D Model of Impeller mould.

1) Apply Mould material as Silica Sand & Apply interface between mould and Casting




Figure 2 Interfaces between Mould and Casting

2) Applying initial conditions for casting and run parameter for impeller simulation.

B. Post Processing Results in VIEW CAST

Obtain the temperature contour in different steps viz. 0, 10, 15, 20, 25, 35 steps and up to 150 steps.




Fig.3. Temperature contour at 150 step

C. Fraction Solid

Fraction of solid is obtained after temperature contour at 150 step, and fig 4 shows fraction of solid




Fig.4. Fraction solid

Above Fraction Solid Figure Shows that after completion of Mould Filling there is a possibility of uneven solidification because metal in the middle portion of the casting(impeller Hub) are in the liquid stage while outside of the hub it has been cooled.

D. Shrinkage Porosity




Fig.5 shrinkage porosity

VI. FINITE ELEMENT ANALYSIS OF IMPELLER IN PROCAST

A. Meshing of impeller in MESHCAST

It is important to note that working with MeshCAST always begins by opening a file. After the file has been loaded, you begin working at the corresponding work step in the process. From this entry point to the final generation of the tetra mesh, the steps you follow and the MeshCAST tools you use will be the same regardless of the type of input file used.

VII. COMPARISON OF RESULT OF SIMULATION AND FEM

By comparing both the results as shown in following figure the shrinkage chances is as shown by pink dots and to eliminate shrinkage now we increase runner and riser size, in order to eliminate shrinkage defect.

A. Comparison of Experimental and FE Analysis Results




Fig.6.Location of Shrinkage Defect



Fig.7.Location of Shrinkage Porosity

As shown in fig. 6 and fig. 7above FE analysis done by software and actual location of porosity exists at the same region.



VIII. CONCLUSION

From above Experimental and Analytical Results We can say that FE Analysis Results Fairly matches with Experimental Results So FE Analysis are a good tool to replace costly experimental and time consuming costly experimental Work.

REFERENCES

- [1] Mr. K.K.Shaw, Project Director, Rajkot Engineering Cluster Development Project Diagnostic Study Report, Entrepreneurship Development Institute of India, Ahmedabad.
- [2] Numerical Optimization of Casting for Defects Analysis and Minimization: A Review Umesh S. Patil1, Dr. K. H. Inamdar2, IJARSE, Vol 6, Issue 10, October 201.
- [3] Casting Simulation – Best Practices, Dr. B. Ravi, Professor, Mechanical Engineering Department Indian Institute of Technology Bombay Mumbai - 400 076, E-mail: b.ravi@iitb.ac.in
- [4] A. G. Thakare1 Research Scholar, G.H.Raisoni College of Engineering Nagpur, India, Data Mining for Casting Defects Analysis, International Journal of Engineering Research & Technology (IJERT), Vol. 2 Issue 12, December – 2013, IJERT/IJERT,ISSN: 2278-0181
- [5] Atul A. Bhujugade1, Minimization of Casting Defects Using Casting Simulation Technique and Casting Defects Analysis Using Design of Experiment, International Journal for Research in Applied Science & Engineering Technology (IJRASET), Volume 3 Issue VI, June 2015, ISSN: 2321-9653
- [6] Dr. B. Ravi, Professor Mechanical Engineering Department Indian Institute of Technology Bombay, Mumbai-400076 E-mail: b.ravi@iitb.ac.in, Phone: +91 22 2576 7510, A Holistic Approach to Zero Defect Castings, Technical Paper for 59TH INDIAN FOUNDRY CONGRESS, Chandigarh, February 2011
- [7] Numerical Optimization of Casting for Defects Analysis and Minimize Dipesh S. Patil1, Dr. M. H. Inamdar2, IJARSE, Vol 7, Issue 7, October 2011.
- [8] Vivek S. Gondkar1, Optimization of Casting Process Parameters through Simulation International Journal of Application or Innovation in Engineering & Management (IJAIEM) Web Site: www.ijaiem.org Email: editor@ijaiem.org Volume 3, Issue 6, June 2014 ISSN 2319 – 4847
- [9] Dr. B. Ravi, Professor Mechanical Engineering Department Indian Institute of Technology Bombay, Mumbai-400076 E-mail: b.ravi@iitb.ac.in, Phone: +91 22 2576 7510, zero defect casting, Technical Paper for 59TH INDIAN FOUNDRY CONGRESS, Chandigarh, February 2012.
- [10] Umesh S. Patil1 Numerical Simulation for Casting Defect Prediction of Steel Casting -A Case Study www.ijert.org © 2017 IJCRT | olume 5, Issue 4 November 2017 | ISSN: 2320-2882
- [11] Prof.B.Ravi, " casting simulation and optimization-advantages and bottle necks" ,Indian Foundry Journal, pp 3-5, 2008



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)